OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
857-5209
Component
Diesel Engine
Fluid
CHEVRON DELO 400 SAE 10W30 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

WEAR

Metal levels are typical for a new component breaking in.

CONTAMINATION

There is no indication of any contamination in the oil.

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		RPL0013909	---	---
Sample Date		Client Info		12 Jan 2024	---	---
Machine Age	hrs	Client Info		604	---	---
Oil Age	hrs	Client Info		0	---	---
Filter Age	hrs	Client Info		0	---	---
Oil Changed		Client Info		Not Changd	---	---
Filter Changed		Client Info		Not Changd	---	---
Sample Status				NORMAL	---	---
Iron	ppm	ASTM D5185m	>100	6	---	---
Chromium	ppm	ASTM D5185m	>20	0	---	---
Nickel	ppm	ASTM D5185m	>4	0	---	---
Titanium	ppm	ASTM D5185m		<1	---	---
Silver	ppm	ASTM D5185m	>3	0	---	---
Aluminum	ppm	ASTM D5185m	>20	4	---	---
Lead	ppm	ASTM D5185m	>40	<1	---	---
Copper	ppm	ASTM D5185m	>330	4	---	---
Tin	ppm	ASTM D5185m	>15	0	---	---
Vanadium	ppm	ASTM D5185m		0	---	---
White Metal	scalar	*Visual	NONE	NONE	---	---
Yellow Metal	scalar	*Visual	NONE	NONE	---	---
Silicon	ppm	ASTM D5185m	>25	9	---	---
Potassium	ppm	ASTM D5185m	>20	11	---	---
Fuel		WC Method	>5	<1.0	---	---
Water		WC Method	>0.2	NEG	---	---
Glycol		WC Method		NEG	---	---
Soot %	%	*ASTM D7844	>3	0.1	---	---
Nitration	Abs/cm	*ASTM D7624	>20	5.3	---	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.0	---	---
Silt	scalar	*Visual	NONE	NONE	---	---
Debris	scalar	*Visual	NONE	NONE	---	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---	---
Appearance	scalar	*Visual	NORML	NORML	---	---
Odor	scalar	*Visual	NORML	NORML	---	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---	---
Sodium	ppm	ASTM D5185m		2	---	---
Boron	ppm	ASTM D5185m		64	---	---
Barium	ppm	ASTM D5185m		0	---	---
Molybdenum	ppm	ASTM D5185m		37	---	---
Manganese	ppm	ASTM D5185m		<1	---	---
Magnesium	ppm	ASTM D5185m		492	---	---
Calcium	ppm	ASTM D5185m		1574	---	---
Phosphorus	ppm	ASTM D5185m	1260	724	---	---
Zinc	ppm	ASTM D5185m	1400	853	---	---
Sulfur	ppm	ASTM D5185m		2460	---	---
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.2	---	---
Base Number (BN)	mg KOH/g	ASTM D2896	10.1	10.0	---	---
Visc @ 100°C	cSt	ASTM D445	11.1	10.8	---	---

Base Number



Viscosity @ 100°C



Ferrous Alloys



Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory	: WearCheck USA - 501 Madison Ave., Cary, NC 27513		
Sample No.	: RPL0013909	**Recieved**	: 30 Jan 2024
Lab Number	: 06073536	**Diagnosed**	: 30 Jan 2024
Unique Number	: 10850213	**Diagnostician**	: Wes Davis
Test Package	: FLEET		

To discuss this sample report, contact Customer Service at 1-800-237-1369.
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

RTL PACLEASE - 7001 - Houston
6300 N. Loop East
Houston, TX
US 77026
Contact: RODNEY BRIGGS
briggsr@rushenterprises.com
T:
F: