WEAR CONTAMINATION **FLUID CONDITION**

NORMAL NORMAL NORMAL

MAX

VOLVO PENTA 7008592381

Port Diesel Engine

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
TEGOMMENDATION	Sample Number	OOM	Client Info	Little	VPA058009		
Resample at the next service interval to monitor.	Sample Date		Client Info		18 Jan 2024		
	Machine Age	hrs	Client Info		89		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAR	Iron	nnm	ASTM D5185m	_8n	14		
WLAN	Chromium	ppm	ASTM D5185m		<1		
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		2		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		<1		
	Aluminum	ppm	ASTM D5185m		2		
	Lead	ppm	ASTM D5185m		<1		
	Copper	ppm	ASTM D5185m		35		
	Tin	ppm	ASTM D5185m		<1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	O'll'		AOTM DEADE	05	45		
	Silicon	ppm	ASTM D5185m		15 10		
There is no indication of any contamination in the oil.	Potassium Fuel	ppm	ASTM D5185m				
			WC Method		<1.0 NEG		
	Water		WC Method WC Method	>0.1	NEG		
	Glycol Soot %	%	*ASTM D7844		0.3		
	Nitration	Abs/cm	*ASTM D7624	> 20	5.8		
	Sulfation	Abs/.1mm	*ASTM D7024		19.1		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water		*Visual	>0.1	NEG		
THIR CONDITION	Ca alicena		ACTM DE105		•		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		3		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		94		
	Barium	ppm	ASTM D5185m ASTM D5185m		0 67		
	Molybdenum	ppm			67		
	Manganese Magnesium	ppm	ASTM D5185m		<1 426		
	Calcium	ppm	ASTM D5185m		436 1630		
	Phosphorus	ppm	ASTM D5185m ASTM D5185m		1630 916		
	Zinc	ppm	ASTM D5165III		1175		
	Sulfur	ppm	ASTM D5185m		3749		
	Oxidation	Abs/.1mm	*ASTM D3163111	>25	14.3		
	Base Number (BN)			723	9.1		
	Dasc Nulliber (DIV)	my Norly	10 LINI D5030		J. I		





Report Id: VP694356 [WUSCAR] 06073714 (Generated: 01/31/2024 21:35:00) Rev: 1

Laboratory Sample No. Lab Number **Unique Number**

: VPA058009 : 06073714 : 10850391

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 30 Jan 2024 Diagnosed

: 31 Jan 2024 Diagnostician : Don Baldridge

Test Package : MOB 1 (Additional Tests: TBN)

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Marine International Diesels Inc.

3600 HACIENDA BLVD UNIT G DAVIE, FL

US 33314 Contact: ASHANTI BURKE aburke@midiflorida.com

T: (954)761-1086 F: (954)761-1186