
WEAR CONTAMINATION FLUID CONDITION


NORMAL NORMAL


Machine Id HC-2205


Component
2 Swing Drive

DECOMMEND ATION	_					١	
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		WC0873374	WC0746604	
	Sample Date		Client Info		02 Jan 2024	01 Apr 2023	
	Machine Age	hrs	Client Info		7825	7349	
	Oil Age	hrs	Client Info		0	989	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Not Changd	Changed	
	Filter Changed		Client Info		Changed	Changed	
	Sample Status				NORMAL	ATTENTION	
WEAR	Iron	ppm	ASTM D5185m	>400	4	12	
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>10	<1	<1	
	Nickel	ppm	ASTM D5185m		0	0	
	Titanium	ppm	ASTM D5185m		<1	0	
	Silver	ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m	>25	2	0	
	Lead	ppm	ASTM D5185m		<1	<1	
	Copper	ppm	ASTM D5185m		<1	3	
	Tin	ppm	ASTM D5185m		<1	<1	
	Vanadium	ppm	ASTM D5185m		0	0	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
	· · · · · · · · · · · · · · · · · · ·						
CONTAMINATION	Silicon	ppm	ASTM D5185m	>50	3	7	
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	2	<1	
	Water		WC Method	>0.2	NEG	NEG	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m		0	0	
	Boron	ppm	ASTM D5185m	50	8	<1	
The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185m		0	0	
	Molybdenum	ppm	ASTM D5185m	15	<1	<1	
	Manganese	ppm	ASTM D5185m		0	0	
	Magnesium	ppm	ASTM D5185m	50	<1	4	
	Calcium	ppm	ASTM D5185m		3	71	
	Phosphorus	ppm	ASTM D5185m	350	322	298	
	Zinc	ppm	ASTM D5185m		0	186	
	Sulfur	ppm	ASTM D5185m	12500	5582	2977	
	Visc @ 40°C	cSt	ASTM D445		234	▲ 65.0	













Certificate L2367

Laboratory Sample No. Lab Number

: WC0873374 : 06074184 Unique Number : 10856275 Test Package : CONST To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 30 Jan 2024 Diagnosed : 31 Jan 2024 Diagnostician : Wes Davis

BUCKNER HEAVY LIFT 4732 NC 54 EAST GRAHAM, NC US 27253-9215

Contact: MICHAEL LAWSON michaell@bucknercompanies.com T: (336)376-8888

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (336)376-4090