



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
Store 9 - Marietta
Machine Id
JOHN DEERE 250G EX39 (S/N 1FF250GXPNF611949)
Component
Diesel Engine
Fluid
JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (5 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		LEC0047656	LEC0043823	LEC0040456
Sample Date		Client Info		15 Dec 2023	16 Aug 2023	06 Apr 2023
Machine Age	hrs	Client Info		2457	1906	1308
Oil Age	hrs	Client Info		500	500	500
Filter Age	hrs	Client Info		500	500	500
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>51	5	32	42
Chromium	ppm	ASTM D5185m	>11	0	1	2
Nickel	ppm	ASTM D5185m	>5	1	5	2
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>31	3	2	5
Lead	ppm	ASTM D5185m	>26	<1	<1	8
Copper	ppm	ASTM D5185m	>26	0	12	2
Tin	ppm	ASTM D5185m	>4	<1	1	0
Vanadium	ppm	ASTM D5185m		<1	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>120	5	6	5
Potassium	ppm	ASTM D5185m	>20	<1	2	0
Fuel		WC Method	>2.1	<1.0	<1.0	<1.0
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.1	0.6	0.7
Nitration	Abs/cm	*ASTM D7624	>20	5.2	10.1	12.0
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.8	24.5	26.8
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m	>31	2	4	2
Boron	ppm	ASTM D5185m		326	117	6
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		77	101	65
Manganese	ppm	ASTM D5185m		<1	1	<1
Magnesium	ppm	ASTM D5185m		459	557	1013
Calcium	ppm	ASTM D5185m		1431	1635	1196
Phosphorus	ppm	ASTM D5185m		1042	1044	1051
Zinc	ppm	ASTM D5185m		1261	1365	1316
Sulfur	ppm	ASTM D5185m		3270	3589	3819
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.6	19.4	24.9
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	8.6	6.6	6.2
Visc @ 100°C	cSt	ASTM D445	15.4	13.8	14.1	14.1



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : LEC0047656 **Received** : 30 Jan 2024
Lab Number : 06074334 **Diagnosed** : 31 Jan 2024
Unique Number : 10856425 **Diagnostician** : Sean Felton
Test Package : CONST (Additional Tests: TBN)

LANE PIPELINE
 2946 E MAIN ST
 BRIDGEPORT, WV
 US 26330
 Contact: JESSE WILBURN
 jesseowilburn@gmail.com
 T: (740)440-0927
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)