



|                 |               |
|-----------------|---------------|
| WEAR            | <b>NORMAL</b> |
| CONTAMINATION   | <b>NORMAL</b> |
| FLUID CONDITION | <b>NORMAL</b> |

Area  
**[JASON BUSHONG]**  
 Machine Id  
**JOHN DEERE 6129M C318901 (S/N 1LV6129MPLG982725)**  
 Component  
**Diesel Engine**  
 Fluid  
**JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (--- GAL)**

### RECOMMENDATION

Resample at the next service interval to monitor.

| Test           | UOM | Method      | Limit/Abn | Current            | History1 | History2 |
|----------------|-----|-------------|-----------|--------------------|----------|----------|
| Sample Number  |     | Client Info |           | <b>JR0196750</b>   | ---      | ---      |
| Sample Date    |     | Client Info |           | <b>26 Jan 2024</b> | ---      | ---      |
| Machine Age    | hrs | Client Info |           | <b>636</b>         | ---      | ---      |
| Oil Age        | hrs | Client Info |           | <b>0</b>           | ---      | ---      |
| Filter Age     | hrs | Client Info |           | <b>0</b>           | ---      | ---      |
| Oil Changed    |     | Client Info |           | <b>Changed</b>     | ---      | ---      |
| Filter Changed |     | Client Info |           | <b>Changed</b>     | ---      | ---      |
| Sample Status  |     |             |           | <b>NORMAL</b>      | ---      | ---      |

### WEAR

Metal levels are typical for a new component breaking in.

|              |        |             |      |              |     |     |
|--------------|--------|-------------|------|--------------|-----|-----|
| Iron         | ppm    | ASTM D5185m | >51  | <b>11</b>    | --- | --- |
| Chromium     | ppm    | ASTM D5185m | >11  | <b>&lt;1</b> | --- | --- |
| Nickel       | ppm    | ASTM D5185m | >5   | <b>&lt;1</b> | --- | --- |
| Titanium     | ppm    | ASTM D5185m |      | <b>0</b>     | --- | --- |
| Silver       | ppm    | ASTM D5185m | >3   | <b>0</b>     | --- | --- |
| Aluminum     | ppm    | ASTM D5185m | >31  | <b>7</b>     | --- | --- |
| Lead         | ppm    | ASTM D5185m | >26  | <b>&lt;1</b> | --- | --- |
| Copper       | ppm    | ASTM D5185m | >26  | <b>&lt;1</b> | --- | --- |
| Tin          | ppm    | ASTM D5185m | >4   | <b>&lt;1</b> | --- | --- |
| Vanadium     | ppm    | ASTM D5185m |      | <b>&lt;1</b> | --- | --- |
| White Metal  | scalar | *Visual     | NONE | <b>NONE</b>  | --- | --- |
| Yellow Metal | scalar | *Visual     | NONE | <b>NONE</b>  | --- | --- |

### CONTAMINATION











There is no indication of any contamination in the oil.

|                  |          |             |       |                |     |     |
|------------------|----------|-------------|-------|----------------|-----|-----|
| Silicon          | ppm      | ASTM D5185m | >22   | <b>5</b>       | --- | --- |
| Potassium        | ppm      | ASTM D5185m | >20   | <b>7</b>       | --- | --- |
| Fuel             |          | WC Method   | >2.1  | <b>&lt;1.0</b> | --- | --- |
| Water            |          | WC Method   | >0.21 | <b>NEG</b>     | --- | --- |
| Glycol           |          | WC Method   |       | <b>NEG</b>     | --- | --- |
| Soot %           | %        | *ASTM D7844 | >3    | <b>0.2</b>     | --- | --- |
| Nitration        | Abs/cm   | *ASTM D7624 | >20   | <b>8.4</b>     | --- | --- |
| Sulfation        | Abs/.1mm | *ASTM D7415 | >30   | <b>21.3</b>    | --- | --- |
| Silt             | scalar   | *Visual     | NONE  | <b>NONE</b>    | --- | --- |
| Debris           | scalar   | *Visual     | NONE  | <b>NONE</b>    | --- | --- |
| Sand/Dirt        | scalar   | *Visual     | NONE  | <b>NONE</b>    | --- | --- |
| Appearance       | scalar   | *Visual     | NORML | <b>NORML</b>   | --- | --- |
| Odor             | scalar   | *Visual     | NORML | <b>NORML</b>   | --- | --- |
| Emulsified Water | scalar   | *Visual     | >0.21 | <b>NEG</b>     | --- | --- |

### FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

|                  |          |             |      |              |     |     |
|------------------|----------|-------------|------|--------------|-----|-----|
| Sodium           | ppm      | ASTM D5185m | >31  | <b>1</b>     | --- | --- |
| Boron            | ppm      | ASTM D5185m |      | <b>276</b>   | --- | --- |
| Barium           | ppm      | ASTM D5185m |      | <b>&lt;1</b> | --- | --- |
| Molybdenum       | ppm      | ASTM D5185m |      | <b>258</b>   | --- | --- |
| Manganese        | ppm      | ASTM D5185m |      | <b>&lt;1</b> | --- | --- |
| Magnesium        | ppm      | ASTM D5185m |      | <b>826</b>   | --- | --- |
| Calcium          | ppm      | ASTM D5185m |      | <b>1372</b>  | --- | --- |
| Phosphorus       | ppm      | ASTM D5185m |      | <b>911</b>   | --- | --- |
| Zinc             | ppm      | ASTM D5185m |      | <b>1114</b>  | --- | --- |
| Sulfur           | ppm      | ASTM D5185m |      | <b>2950</b>  | --- | --- |
| Oxidation        | Abs/.1mm | *ASTM D7414 | >25  | <b>15.6</b>  | --- | --- |
| Base Number (BN) | mg KOH/g | ASTM D2896  | 13.6 | <b>8.6</b>   | --- | --- |
| Visc @ 100°C     | cSt      | ASTM D445   | 15.4 | <b>14.0</b>  | --- | --- |



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : JR0196750 **Received** : 30 Jan 2024  
**Lab Number** : 06074350 **Diagnosed** : 31 Jan 2024  
**Unique Number** : 10856441 **Diagnostician** : Wes Davis  
**Test Package** : MOBCE ( Additional Tests: TBN )

**JRE - STEPHENSON**  
 245 YARDMASTER COURT  
 STEPHENSON, VA  
 US 22656-1761  
 Contact: PHIL DAUGHERTY  
 pdaugherty@jamesriverequipment.com  
 T: x:  
 F: (540)693-2588

To discuss this sample report, contact Customer Service at 1-800-237-1369.  
 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.  
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)