



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>



Area  
**(GAC711)**  
Machine Id  
**913015**  
Component  
**Diesel Engine**  
Fluid  
**PETRO CANADA DURON SHP 15W40 (11 GAL)**

**RECOMMENDATION**

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>GFL0103411</b>	GFL0092456	GFL0092478
Sample Date		Client Info		<b>24 Jan 2024</b>	11 Dec 2023	04 Oct 2023
Machine Age	hrs	Client Info		<b>3657</b>	3584	3038
Oil Age	hrs	Client Info		<b>73</b>	546	198
Filter Age	hrs	Client Info		<b>73</b>	546	198
Oil Changed		Client Info		<b>Changed</b>	Changed	Changed
Filter Changed		Client Info		<b>Changed</b>	Changed	Changed
Sample Status				<b>NORMAL</b>	ATTENTION	ABNORMAL

**WEAR**

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>120	<b>4</b>	11	10
Chromium	ppm	ASTM D5185m	>20	<b>&lt;1</b>	<1	<1
Nickel	ppm	ASTM D5185m	>5	<b>9</b>	▲ 8	▲ 12
Titanium	ppm	ASTM D5185m	>2	<b>0</b>	0	0
Silver	ppm	ASTM D5185m	>2	<b>0</b>	0	0
Aluminum	ppm	ASTM D5185m	>20	<b>2</b>	1	7
Lead	ppm	ASTM D5185m	>40	<b>&lt;1</b>	0	<1
Copper	ppm	ASTM D5185m	>330	<b>&lt;1</b>	2	4
Tin	ppm	ASTM D5185m	>15	<b>&lt;1</b>	<1	<1
Vanadium	ppm	ASTM D5185m		<b>&lt;1</b>	0	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

**CONTAMINATION**







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	<b>3</b>	3	5
Potassium	ppm	ASTM D5185m	>20	<b>2</b>	2	1
Fuel		WC Method	>3.0	<b>&lt;1.0</b>	0.2	<1.0
Water		WC Method	>0.2	<b>NEG</b>	NEG	NEG
Glycol		WC Method		<b>NEG</b>	NEG	NEG
Soot %	%	*ASTM D7844	>4	<b>0.1</b>	0.4	0.3
Nitration	Abs/cm	*ASTM D7624	>20	<b>5.3</b>	7.6	6.3
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>17.2</b>	18.3	17.7
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	<b>NEG</b>	NEG	NEG

**FLUID CONDITION**

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>3</b>	3	4
Boron	ppm	ASTM D5185m	0	<b>11</b>	2	5
Barium	ppm	ASTM D5185m	0	<b>0</b>	0	0
Molybdenum	ppm	ASTM D5185m	60	<b>53</b>	51	68
Manganese	ppm	ASTM D5185m	0	<b>&lt;1</b>	0	<1
Magnesium	ppm	ASTM D5185m	1010	<b>810</b>	728	914
Calcium	ppm	ASTM D5185m	1070	<b>1108</b>	845	1064
Phosphorus	ppm	ASTM D5185m	1150	<b>973</b>	765	1023
Zinc	ppm	ASTM D5185m	1270	<b>1173</b>	970	1228
Sulfur	ppm	ASTM D5185m	2060	<b>3022</b>	2551	3346
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>12.7</b>	13.8	13.6
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	<b>8.5</b>	5.9	7.9
Visc @ 100°C	cSt	ASTM D445	15.4	<b>13.6</b>	▲ 12.0	13.8



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : GFL0103411 **Received** : 30 Jan 2024  
**Lab Number** : 06074383 **Diagnosed** : 31 Jan 2024  
**Unique Number** : 10856474 **Diagnostician** : Wes Davis  
**Test Package** : FLEET

**GFL Environmental - 095 - Atlanta West**  
 2699 Cochran Industrial Blvd  
 Douglasville, GA  
 US 30127-1332  
 Contact: Darrell Welch  
 darrell.welch@gflenv.com  
 T: (800)207-6618  
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)