

**WEAR** CONTAMINATION **FLUID CONDITION** 

**NORMAL ABNORMAL NORMAL** 

## **SULLAIR 80017 - QUIKERET**

Component Compressor

OC III TRA PI IIS (--- GAL)

QC ULTRA PLUS ( GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		TO50001863		
The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.	Sample Date		Client Info		05 Jan 2024		
	Machine Age	hrs	Client Info		28631		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Changed		
	Sample Status				ABNORMAL		
WEAR	Iron	nnm	ASTM D5185m	<u>~50</u>	<1		
WEAN	Chromium	ppm	ASTM D5185m		<1		
All component wear rates are normal.	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>25	2		
	Lead	ppm	ASTM D5185m		- <1		
	Copper	ppm	ASTM D5185m		3		
	Tin	ppm	ASTM D5185m	>15	<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m		2		
There is a binds area and of montional data area and in the cit	Potassium	ppm	ASTM D5185m		3		
There is a high amount of particulates present in the oil.	Water	%	ASTM D6304	>0.1	0.063		
	ppm Water	ppm	ASTM D6304		631		
	Particles >4µm		ASTM D7647		▲ 81373		
	Particles >6µm		ASTM D7647		<u>▲</u> 33882		
	Particles >14µm		ASTM D7647	>320	▲ 3415 ▲ 500		
	Particles >21µm		ASTM D7647		<u> </u>		
	Particles >38µm Particles >71µm		ASTM D7647 ASTM D7647		4 0		
	Oil Cleanliness		ISO 4406 (c)	>20/18/15	<u>4</u> 24/22/19		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	LIGHT		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		46		
	Boron	ppm	ASTM D5185m		0		
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		38		
	Molybdenum	ppm	ASTM D5185m		<1		
	Manganese	ppm	ASTM D5185m		0		
	Magnesium	ppm	ASTM D5185m		2		
	Calcium	ppm	ASTM D5185m		7		
	Phosphorus	ppm	ASTM D5185m		263		
	Zinc	ppm	ASTM D5185m ASTM D5185m		0 52		
	Culfur		MCXI CU IVII CH		57		
	Sulfur	ppm ma KOH/a					
	Acid Number (AN)	mg KOH/g	ASTM D8045		0.23		

Contact/Location: SEAN ? - QUAALV





Certificate L2367

Laboratory Sample No. Lab Number

**Unique Number** 

: TO50001863 : 06074689 : 10856780

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 30 Jan 2024 Diagnosed : 01 Feb 2024

Diagnostician : Jonathan Hester Test Package : IND 2 ( Additional Tests: KF, KV100, PrtCount, VI ) To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) **QUALITY COMPRESSOR** 

4428 CR 616 ALVARADO, TX US 76009 Contact: SEAN

SEAN@QCOMPRESSOR.COM T: (817)822-1333

Contact/Location: SEAN ? - QUAALV

F: