

WEAR CONTAMINATION FLUID CONDITION


NORMAL ABNORMAL NORMAL

QUINCY 88362 - BUILDERS 1ST DALLAS

Component Compressor

Compressor Pluid QUINCY QUINSYN (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
RECOMMENDATION	Sample Number	UCIVI	Client Info	LIIIIUADII	TO50001868	,	QUC0000472
No corrective action is recommended at this time. Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor.	Sample Date		Client Info		24 Jan 2024	24 Oct 2023	14 Jul 2023
	Machine Age	hrs	Client Info		16381	0	15580
	Oil Age	hrs	Client Info		0	10	0
	Filter Age	hrs	Client Info		0	3	0
	Oil Changed		Client Info		Changed	Not Changd	Not Changd
	Filter Changed		Client Info		Changed	Changed	Changed
	Sample Status				ABNORMAL	ABNORMAL	SEVERE
WEAR	Iron	ppm	ASTM D5185m	>50	12	6	
	Chromium	ppm	ASTM D5185m	>10	<1	0	
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		0	0	
	Titanium	ppm	ASTM D5185m		<1	0	
	Silver	ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m		2	3	
	Lead	ppm	ASTM D5185m		0	0	
	Copper	ppm	ASTM D5185m		2	0	
	Tin	ppm	ASTM D5185m	>15	<1	<1	
	Vanadium	ppm	ASTM D5185m	NONE	0	0	
	White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185m	>25	<1	2	
	Potassium	ppm	ASTM D5185m	>20	3	1	
There is a high amount of particulates present in the oil. The water content is negligible.	Water	%	ASTM D6304	>0.1	0.007	0.005	90.0
	ppm Water	ppm	ASTM D6304	>1000	80	53.0	900000
	Particles >4µm		ASTM D7647	>10000	82389	<u> </u>	
	Particles >6µm		ASTM D7647		<u> </u>	<u> </u>	
	Particles >14μm		ASTM D7647		<u>^</u> 621	<u></u> 3160	
	Particles >21µm		ASTM D7647		<u> </u>	<u>▲</u> 726	
	Particles >38μm		ASTM D7647		2	<u>19</u>	
	Particles >71µm		ASTM D7647		0	1	
	Oil Cleanliness Silt	acalar	ISO 4406 (c) *Visual	>20/18/15 NONE	A 24/22/16 NONE	A 24/22/19 NONE	NONE
	Debris	scalar scalar	*Visual	NONE	NONE	LIGHT	▲ MODER
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
	Odor	scalar	*Visual	NORML	NORML	NORML	NORML
	Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	0.2%
FLUID CONDITION	Sodium	ppm	ASTM D5185m		<1	4	
TEOID CONDITION	Boron	ppm	ASTM D5185m		0	0	
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0	0	
	Molybdenum	ppm	ASTM D5185m		<1	0	
	Manganese	ppm	ASTM D5185m		<1	<1	
	Magnesium	ppm	ASTM D5185m		<1	<1	
	Calcium	ppm	ASTM D5185m		0	2	
	Phosphorus	ppm	ASTM D5185m		82	99	
	Zinc	ppm	ASTM D5185m		67	47	
	Sulfur	ppm	ASTM D5185m		903	837	
	Acid Number (AN)	mg KOH/g	ASTM D8045		0.28	0.25	
	Visc @ 40°C	cSt	ASTM D445		50.6	49.8	
	Visc @ 100°C	cSt	ASTM D445		8.5	8.3	
	Viscosity Index (VI)	Scale	ASTM D2270	132	144	140	

Contact/Location: SEAN ? - QUAALV





Certificate L2367

Laboratory Sample No.

Lab Number **Unique Number**

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : TO50001868 : 06074708 : 10856799

Recieved

: 30 Jan 2024 Diagnosed : 01 Feb 2024 Diagnostician : Jonathan Hester Test Package : IND 2 (Additional Tests: KF, KV100, PrtCount, VI)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) **QUALITY COMPRESSOR**

4428 CR 616 ALVARADO, TX US 76009 Contact: SEAN

SEAN@QCOMPRESSOR.COM T: (817)822-1333

Contact/Location: SEAN ? - QUAALV

F: