



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
SOUTH HOLLAND
Machine Id
TEREX RT665 RT4133 (S/N 14133)
Component
Diesel Engine
Fluid
DIESEL ENGINE OIL 10W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		HPL0004137	HPL0002281	HPL0001455
Sample Date		Client Info		27 Jan 2024	07 Feb 2023	26 May 2022
Machine Age	hrs	Client Info		4265	3426	2865
Oil Age	hrs	Client Info		0	730	0
Filter Age	hrs	Client Info		0	730	0
Oil Changed		Client Info		N/A	Changed	N/A
Filter Changed		Client Info		N/A	Changed	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	26	14	25
Chromium	ppm	ASTM D5185m	>20	<1	<1	1
Nickel	ppm	ASTM D5185m	>4	<1	<1	0
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	6	2	4
Lead	ppm	ASTM D5185m	>40	2	1	3
Copper	ppm	ASTM D5185m	>330	2	2	2
Tin	ppm	ASTM D5185m	>15	0	0	<1
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	19	8	11
Potassium	ppm	ASTM D5185m	>20	2	1	1
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.2	0.2	0.2
Nitration	Abs/cm	*ASTM D7624	>20	14.1	11.5	10.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	39.5	31.3	29.4
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	LIGHT
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		0	<1	<1
Boron	ppm	ASTM D5185m	250	2	14	229
Barium	ppm	ASTM D5185m	10	4	0	<1
Molybdenum	ppm	ASTM D5185m	100	558	436	699
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m	450	959	896	447
Calcium	ppm	ASTM D5185m	3000	2459	2294	3878
Phosphorus	ppm	ASTM D5185m	1150	1056	1034	845
Zinc	ppm	ASTM D5185m	1350	1208	1227	1061
Sulfur	ppm	ASTM D5185m	4250	10343	7038	16881
Oxidation	Abs/.1mm	*ASTM D7414	>25	44.9	32.5	20.5
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	12.84	14.96	14.9
Visc @ 100°C	cSt	ASTM D445	14.4	13.8	14.1	14.1



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : HPL0004137 **Received** : 30 Jan 2024
Lab Number : 06075015 **Diagnosed** : 01 Feb 2024
Unique Number : 10857106 **Diagnostician** : Sean Felton
Test Package : MOB 2

STEVENS ON CRANE
 410 STEVENSON DR
 BOLINGBROOK, IL
 US 60440
 Contact: DAVE KOEHNE
 davidk@stevensoncrane.com
 T: (630)972-9199
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)