

# **ASCENDUM 500 HR CSA** Drop Box

# VOLVO A40G 2346 (S/N A40GV752044)

## VOLVO SUPER GEAR OIL 75W-80-GO102 (--- GAL)

Visc @ 40°C

cSt

ASTM D445

RECOMMENDATION

No corrective action is recommended at this time. Resample at the next service interval to monitor.

	_		
			- 1
w w		^ •	-1

All component wear rates are normal.

### **CONTAMINATION**

Moderate concentration of visible dirt/debris present in the oil.


### **FLUID CONDITION**

The condition of the oil is acceptable for the time in service.

00-00102	<b>.</b>			~~~~~		
Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		ASC0007931		
Sample Date		Client Info		29 Jan 2024		
Machine Age	hrs	Client Info		494		
Oil Age	hrs	Client Info		494		
Filter Age	hrs	Client Info		0		
Oil Changed		Client Info		Not Changd		
Filter Changed		Client Info		None		
Sample Status				ABNORMAL		
Iron	ppm	ASTM D5185m	>500	32		
Chromium	ppm	ASTM D5185m	>20	<1		
Nickel	ppm	ASTM D5185m	>10	<1		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>30	2		
Lead	ppm	ASTM D5185m	>30	0		
Copper	ppm	ASTM D5185m	>30	<1		
Tin	ppm	ASTM D5185m	>20	0		
Vanadium	ppm	ASTM D5185m		0		
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Ciliana				0		
Silicon	ppm	ASTM D5185m	>50	3 3		
Potassium	ppm	ASTM D5185m	>20	-		
Water	eeelex	WC Method	>0.2	NEG		
Silt	scalar	*Visual	NONE			
Debris	scalar	*Visual	NONE			
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Sodium	ppm	ASTM D5185m		0		
Boron	ppm	ASTM D5185m		292		
Barium	ppm	ASTM D5185m		2		
Molybdenum	ppm	ASTM D5185m		2		
Manganese	ppm	ASTM D5185m		4		
Magnesium	ppm	ASTM D5185m		2		
Calcium	ppm	ASTM D5185m		_ 160		
Phosphorus	ppm	ASTM D5185m		2269		
Zinc	ppm	ASTM D5185m		73		
Sulfur	ppm	ASTM D5185m		30055		
	- 01			50.0		

Submitted By: KARRINGTON RENDLEMAN

52.6



Ferrous Alloys 32 30 28 nickel 26 24 22 20 18 ۲G 16 14 12 10 Non-ferrous Metals 10 lead maa Viscosity @ 40°C 90 85 80 7! cSt (40°C) 6! 60 55 50 Jan29/24 Jan29/24

> TRIANGLE GRADING AND PAVING INC 1521 Huffman Mill Rd BURLINGTON, NC US 27216 Contact: KAREN HILLIARD khilliard@trianglegradingpaving.com T: (336)584-1745 GM 106:2012) F: (336)584-0145



 Unique Number
 : 10858252
 Diagnostician
 : Sean Felton

 Certificate 12367
 Test Package
 : CONST

 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 khilliard

 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

: ASC0007931

: 06076161

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

: 31 Jan 2024

: 02 Feb 2024

Recieved

Diagnosed

Report Id: TRIBUR [WUSCAR] 06076161 (Generated: 02/02/2024 10:14:05) Rev: 1

Laboratory

Sample No.

Lab Number

Submitted By: KARRINGTON RENDLEMAN

Page 2 of 2