



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
(P858111)
Machine Id
713011
Component
Diesel Engine
Fluid
DIESEL ENGINE OIL SAE 40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0096909	GFL0050907	GFL0050896
Sample Date		Client Info		29 Jan 2024	01 Nov 2023	01 Sep 2023
Machine Age	hrs	Client Info		2321	2321	1871
Oil Age	hrs	Client Info		0	1720	151
Filter Age	hrs	Client Info		0	1720	151
Oil Changed		Client Info		Not Changd	Changed	Not Changd
Filter Changed		Client Info		Not Changd	Changed	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>120	<1	15	4
Chromium	ppm	ASTM D5185m	>20	0	<1	<1
Nickel	ppm	ASTM D5185m	>5	<1	<1	0
Titanium	ppm	ASTM D5185m	>2	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>20	2	3	1
Lead	ppm	ASTM D5185m	>40	0	<1	0
Copper	ppm	ASTM D5185m	>330	0	4	2
Tin	ppm	ASTM D5185m	>15	<1	<1	0
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	2	4	3
Potassium	ppm	ASTM D5185m	>20	<1	9	2
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>4	0.1	0.4	0.2
Nitration	Abs/cm	*ASTM D7624	>20	4.8	8.7	5.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	17.4	19.9	17.3
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>216	0	2	2
Boron	ppm	ASTM D5185m	250	10	7	19
Barium	ppm	ASTM D5185m	10	<1	<1	0
Molybdenum	ppm	ASTM D5185m	100	57	66	68
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m	450	865	907	941
Calcium	ppm	ASTM D5185m	3000	972	1137	1203
Phosphorus	ppm	ASTM D5185m	1150	970	981	1047
Zinc	ppm	ASTM D5185m	1350	1160	1206	1228
Sulfur	ppm	ASTM D5185m	4250	2878	2856	3755
Oxidation	Abs/.1mm	*ASTM D7414	>25	12.7	16.1	12.8
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	8.8	6.8	8.4
Visc @ 100°C	cSt	ASTM D445	14.4	13.7	12.9	13.3



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0096909 **Received** : 01 Feb 2024
Lab Number : 06076587 **Diagnosed** : 01 Feb 2024
Unique Number : 10858678 **Diagnostician** : Wes Davis
Test Package : FLEET

GFL Environmental - 031 - Greenville/Spartanburg
 1635 Antioch Church Rd
 Piedmont, SC
 US 29673
 Contact: TECHNICIAN ACCOUNT
 catherine.anastasio@wearcheck.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: