



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
PLANT 1 [907260196]
Machine Id
AIR COMP 4 (S/N M0X10028144)
Component
Air Compressor
Fluid
INGERSOLL-RAND ULTRA FG (8 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		PCA0103374	PCA0071501	PCA0060087
Sample Date		Client Info		23 Jan 2024	02 Feb 2023	09 Aug 2022
Machine Age	hrs	Client Info		23659	15743	12008
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Chngd	Not Chngd	Not Chngd
Filter Changed		Client Info		Not Chngd	Not Chngd	Not Chngd
Sample Status				NORMAL	NORMAL	ABNORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	0	0	<1
Chromium	ppm	ASTM D5185m	>4	0	0	0
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>10	0	0	<1
Lead	ppm	ASTM D5185m	>20	<1	<1	0
Copper	ppm	ASTM D5185m	>40	<1	<1	0
Tin	ppm	ASTM D5185m	>5	<1	<1	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION










There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

Silicon	ppm	ASTM D5185m	>25	<1	<1	0
Potassium	ppm	ASTM D5185m	>20	7	7	2
Water		WC Method	>0.6	NEG	NEG	NEG
Particles >4µm		ASTM D7647	>10000	7187	737	▲ 42017
Particles >6µm		ASTM D7647	>2500	926	130	▲ 8308
Particles >14µm		ASTM D7647	>320	19	8	▲ 442
Particles >21µm		ASTM D7647	>80	4	1	62
Particles >38µm		ASTM D7647	>20	0	0	2
Particles >71µm		ASTM D7647	>4	0	0	0
Oil Cleanliness		ISO 4406 (c)	>20/18/15	20/17/11	17/14/10	▲ 23/20/16
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	LIGHT	NONE	VLITE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.6	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		34	22	22
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		8	18	22
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		<1	<1	0
Magnesium	ppm	ASTM D5185m		0	2	1
Calcium	ppm	ASTM D5185m		8	72	59
Phosphorus	ppm	ASTM D5185m		178	186	258
Zinc	ppm	ASTM D5185m		<1	12	5
Sulfur	ppm	ASTM D5185m		379	567	487
Acid Number (AN)	mg KOH/g	ASTM D8045		0.60	0.68	0.34
Visc @ 40°C	cSt	ASTM D445	46.0	58.8	59.8	54.5



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0103374 **Received** : 01 Feb 2024
Lab Number : 06076830 **Tested** : 02 Feb 2024
Unique Number : 10858921 **Diagnosed** : 02 Feb 2024 - Don Baldrige
Test Package : IND 2 (Additional Tests: PrtCount)

MCCAIN FOODS
 319 RICHARDSON RD
 EASTON, ME
 US 04740
 Contact: HADLEY MCNAMEE
 hadley.mcnamee@mccain.ca
 T: (207)488-1335
 F: (207)488-1249

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)