
**WEAR** CONTAMINATION **FLUID CONDITION**  **NORMAL** NORMAL **NORMAL** 

## Pillen Family Farms Machine Id MILTK38

Component Diesel Engine

	Task	11044	Made - 1	Line St. (A.)	(	I Bakan 4	11!
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		SBP0006176		
	Sample Date	lawa	Client Info		12 Jan 2024		
	Machine Age	hrs	Client Info		350		
	Oil Age	hrs	Client Info		350		
	Filter Age	hrs	Client Info		0 Nat Ohamud		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
VEAR	Iron	ppm	ASTM D5185m	>90	10		
	Chromium	ppm	ASTM D5185m	>20	<1		
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		2		
	Lead	ppm	ASTM D5185m		2		
	Copper	ppm	ASTM D5185m		<1		
	Tin	ppm	ASTM D5185m		1		
	Vanadium	ppm	ASTM D5185m	7.0	0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
			v 150aa1	11011			
CONTAMINATION	Silicon	ppm	ASTM D5185m	>25	3		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	3		
	Fuel		WC Method	>3.0	<1.0		
	Water		WC Method	>0.2	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	*ASTM D7844	>6	0.3		
	Nitration	Abs/cm	*ASTM D7624	>20	8.6		
	Sulfation	Abs/.1mm	*ASTM D7415	>30	20.1		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	<b>Emulsified Water</b>	scalar	*Visual	>0.2	NEG		
I LUD CONDITION	0 "						
LUID CONDITION	Sodium	ppm	ASTM D5185m	0	3		
The BN result indicates that there is suitable alkalinity remaining in the	Boron	ppm	ASTM D5185m		0		
oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m	U	61		
	Manganese	ppm	ASTM D5185m	0	<1		
	Magnesium	ppm	ASTM D5185m	0	918		
	Calcium	ppm	ASTM D5185m		985		
	Phosphorus	ppm	ASTM D5185m		1003		
	Zinc	ppm	ASTM D5185m		1173		
	Sulfur	ppm	ASTM D5185m	05	2736		
	Oxidation	Abs/.1mm	*ASTM D7414		15.7		
	Base Number (BN)		ASTM D2896		7.5		
	Visc @ 100°C	cSt	ASTM D445	14	13.5		







Laboratory Sample No. Lab Number **Unique Number** 

: SBP0006176 : 06077399 : 10859490 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 01 Feb 2024 : 04 Feb 2024 Diagnosed Diagnostician : Don Baldridge

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Pillen Family Farms - 722828 26741 NE-91

Humphrey, NE US 61357 Contact: Troy Runge troyfr@pillenfamilyfarms.com

T: (308)390-6733