WEAR CONTAMINATION FLUID CONDITION **NORMAL NORMAL NORMAL**

Area [W/O 10292]

VOLVO L90H 625919

Component Diesel Engine

VOLVO ULTRA DIESEL ENGINE OIL 15W40 VDS-3 (5 GAL)

VOLVO ULTRA DIESEL ENGINE OIL 15W40 VDS-3 (5 GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
RESSMINERBATION	Sample Number		Client Info	21111071011	ML0000144		
Resample at the next service interval to monitor.	Sample Date		Client Info		05 Feb 2024		
	Machine Age	hrs	Client Info		3630		
	Oil Age	hrs	Client Info		500		
	Filter Age	hrs	Client Info		500		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR All component wear rates are normal.	Iron	ppm	ASTM D5185m		59		
	Chromium	ppm	ASTM D5185m		1		
	Nickel	ppm	ASTM D5185m	>10	<1		
	Titanium	ppm	ASTM D5185m		2		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		5		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		<1		
	Tin	ppm	ASTM D5185m	>10	<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>20	6		
CONTAININATION	Potassium	ppm	ASTM D5185m		0		
There is no indication of any contamination in the oil.	Fuel	ррпп	WC Method		<1.0		
	Water		WC Method		NEG		
	Glycol		WC Method	70.1	NEG		
	Soot %	%	*ASTM D7844	>3	0.4		
	Nitration	Abs/cm	*ASTM D7624	>20	7.9		
	Sulfation	Abs/.1mm	*ASTM D7415		22.4		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		<1		
The BN result indicates that there is suitable alkalinity remaining in the	Boron	ppm	ASTM D5185m		326		
oil. The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		85		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		425		
	Calcium	ppm	ASTM D5185m		1311		
	Phosphorus	ppm	ASTM D5185m		1058		
	Zinc	ppm		1223	1256		
	Sulfur	ppm Abo/1mm	ASTM D5185m		3139		
	Oxidation	Abs/.1mm	*ASTM D7414		16.5		
	Base Number (BN)	0 0	ASTM D2896		6.5		
	Visc @ 100°C	cSt	ASTM D445	15.0	13.5		







Certificate L2367

Report Id: VOLVO0150 [WUSCAR] 06082926 (Generated: 02/09/2024 13:33:40) Rev: 1

Laboratory

Sample No.

: ML0000144 Lab Number : 06082926

Unique Number : 10870371 Test Package : CONST (Additional Tests: TBN)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 07 Feb 2024 **Tested**

: 08 Feb 2024 : 09 Feb 2024 - Don Baldridge Diagnosed

MCCLUNG-LOGAN EQUIPMENT CO - BALTIMORE 4601 WASHINGTON BOULEVARD

 $\mathsf{BALTIMORE},\,\mathsf{MD}$ US 21227

Contact: MARK CIULLA mciulla@mcclung-logan.com

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (410)242-6500 F: (410)242-7835 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Submitted By: DELANO GREGORY