



# OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id  
**JLG 600S PL2708 (S/N 0300262708)**

Component  
**Diesel Engine**

Fluid  
**DIESEL ENGINE OIL 10W40 (2 GAL)**

## RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>HPL0004175</b>	HPL0002373	---
Sample Date		Client Info		<b>05 Feb 2024</b>	16 Dec 2022	---
Machine Age	hrs	Client Info		<b>1943</b>	1469	---
Oil Age	hrs	Client Info		<b>0</b>	403	---
Filter Age	hrs	Client Info		<b>0</b>	403	---
Oil Changed		Client Info		<b>N/A</b>	Changed	---
Filter Changed		Client Info		<b>N/A</b>	Changed	---
Sample Status				<b>NORMAL</b>	NORMAL	---

## WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	<b>14</b>	39	---
Chromium	ppm	ASTM D5185m	>20	<b>1</b>	2	---
Nickel	ppm	ASTM D5185m	>4	<b>0</b>	0	---
Titanium	ppm	ASTM D5185m		<b>0</b>	<1	---
Silver	ppm	ASTM D5185m	>3	<b>0</b>	0	---
Aluminum	ppm	ASTM D5185m	>20	<b>6</b>	7	---
Lead	ppm	ASTM D5185m	>40	<b>0</b>	1	---
Copper	ppm	ASTM D5185m	>330	<b>2</b>	4	---
Tin	ppm	ASTM D5185m	>15	<b>&lt;1</b>	<1	---
Vanadium	ppm	ASTM D5185m		<b>&lt;1</b>	<1	---
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	---
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	---

## CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	<b>10</b>	15	---
Potassium	ppm	ASTM D5185m	>20	<b>0</b>	0	---
Fuel		WC Method	>5	<b>&lt;1.0</b>	<1.0	---
Water		WC Method	>0.2	<b>NEG</b>	NEG	---
Glycol		WC Method		<b>NEG</b>	NEG	---
Soot %	%	*ASTM D7844	>3	<b>0.1</b>	0.1	---
Nitration	Abs/cm	*ASTM D7624	>20	<b>16.2</b>	15.9	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>40.0</b>	33	---
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	---
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	---
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	---
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	---
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	---
Emulsified Water	scalar	*Visual	>0.2	<b>NEG</b>	NEG	---

## FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>2</b>	2	---
Boron	ppm	ASTM D5185m	250	<b>15</b>	235	---
Barium	ppm	ASTM D5185m	10	<b>0</b>	0	---
Molybdenum	ppm	ASTM D5185m	100	<b>567</b>	641	---
Manganese	ppm	ASTM D5185m		<b>&lt;1</b>	1	---
Magnesium	ppm	ASTM D5185m	450	<b>952</b>	500	---
Calcium	ppm	ASTM D5185m	3000	<b>2507</b>	3973	---
Phosphorus	ppm	ASTM D5185m	1150	<b>1041</b>	899	---
Zinc	ppm	ASTM D5185m	1350	<b>1261</b>	1046	---
Sulfur	ppm	ASTM D5185m	4250	<b>9577</b>	19356	---
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>46.1</b>	28.6	---
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	<b>13.28</b>	12.99	---
Visc @ 100°C	cSt	ASTM D445	14.4	<b>14.1</b>	14.2	---



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513

**Sample No.** : HPL0004175

**Lab Number** : 06083151

**Unique Number** : 10870596

**Test Package** : MOB 2

**Received** : 07 Feb 2024

**Tested** : 08 Feb 2024

**Diagnosed** : 09 Feb 2024 - Sean Felton

**STEVENS ON CRANE**

410 STEVENSON DR

BOLINGBROOK, IL

US 60440

Contact: DAVE KOEHNE

davidk@stevensoncrane.com

T: (630)972-9199

F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)