



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
ENG 4C
Component
Biogas Engine
Fluid

AMERICAN REFINING GROUP LOW ASH 40 (110 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0881536	WC0881532	WC0881519
Sample Date		Client Info		05 Feb 2024	29 Jan 2024	26 Dec 2023
Machine Age	hrs	Client Info		82320	82224	81417
Oil Age	hrs	Client Info		239	143	947
Filter Age	hrs	Client Info		239	143	947
Oil Changed		Client Info		N/A	Changed	N/A
Filter Changed		Client Info		N/A	Changed	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>45	3	2	8
Chromium	ppm	ASTM D5185m	>2	<1	<1	1
Nickel	ppm	ASTM D5185m	>2	<1	<1	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>5	0	<1	0
Aluminum	ppm	ASTM D5185m	>10	1	3	2
Lead	ppm	ASTM D5185m	>5	1	3	2
Copper	ppm	ASTM D5185m	>14	2	4	7
Tin	ppm	ASTM D5185m	>13	3	3	4
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>200	120	79	199
Potassium	ppm	ASTM D5185m	>20	2	3	0
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844		0	0	0
Nitration	Abs/cm	*ASTM D7624	>20	4.9	4.5	6.3
Sulfation	Abs/.1mm	*ASTM D7415	>30	16.6	15.6	17.9
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		0	3	5
Boron	ppm	ASTM D5185m		0	1	4
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		3	3	6
Manganese	ppm	ASTM D5185m		0	2	<1
Magnesium	ppm	ASTM D5185m		11	13	49
Calcium	ppm	ASTM D5185m		1237	1223	1307
Phosphorus	ppm	ASTM D5185m		262	306	313
Zinc	ppm	ASTM D5185m		391	379	396
Sulfur	ppm	ASTM D5185m		2593	2675	2645
Oxidation	Abs/.1mm	*ASTM D7414	>25	10.4	9.2	13.6
Acid Number (AN)	mg KOH/g	ASTM D8045		0.81	0.26	1.55
Base Number (BN)	mg KOH/g	ASTM D2896		3.30	3.84	3.04
Visc @ 100°C	cSt	ASTM D445		13.3	13.1	13.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : WC0881536

Lab Number : 06083818

Unique Number : 10871263

Test Package : MOB 2

Received : 08 Feb 2024

Tested : 09 Feb 2024

Diagnosed : 11 Feb 2024 - Don Baldrige

BROOME ENERGY

286 KNAPP ROAD

BINGHAMTON, NY

US 13905

Contact: RUSS MERCER

BroomeEnergy@gmail.com

T: (607)766-0358

F: (607)766-0357

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)