



# OIL ANALYSIS REPORT

WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>



Machine Id  
**BELL B30E B93A631EL03410914**  
Component  
**Rear Right Final Drive**  
Fluid  
**GEAR OIL SAE 80W90 (--- GAL)**

## RECOMMENDATION

The oil change at the time of sampling has been noted. Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>BE0024627</b>	---	---
Sample Date		Client Info		<b>30 Jan 2024</b>	---	---
Machine Age	hrs	Client Info		<b>81</b>	---	---
Oil Age	hrs	Client Info		<b>0</b>	---	---
Filter Age	hrs	Client Info		<b>0</b>	---	---
Oil Changed		Client Info		<b>Changed</b>	---	---
Filter Changed		Client Info		<b>Changed</b>	---	---
Sample Status				<b>NORMAL</b>	---	---

## WEAR

Metal levels are typical for a new component breaking in.

PQ		ASTM D8184	>3000	<b>184</b>	---	---
Iron	ppm	ASTM D5185m	>HR:1=	<b>199</b>	---	---
Chromium	ppm	ASTM D5185m	>10	<b>1</b>	---	---
Nickel	ppm	ASTM D5185m	>10	<b>&lt;1</b>	---	---
Titanium	ppm	ASTM D5185m		<b>&lt;1</b>	---	---
Silver	ppm	ASTM D5185m		<b>0</b>	---	---
Aluminum	ppm	ASTM D5185m	>25	<b>3</b>	---	---
Lead	ppm	ASTM D5185m	>25	<b>&lt;1</b>	---	---
Copper	ppm	ASTM D5185m	>50	<b>75</b>	---	---
Tin	ppm	ASTM D5185m	>10	<b>2</b>	---	---
Vanadium	ppm	ASTM D5185m		<b>0</b>	---	---
White Metal	scalar	*Visual	NONE	<b>NONE</b>	---	---
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	---	---

## CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>201	<b>19</b>	---	---
Potassium	ppm	ASTM D5185m	>20	<b>3</b>	---	---
Water		WC Method	>1.01	<b>NEG</b>	---	---
Silt	scalar	*Visual	NONE	<b>NONE</b>	---	---
Debris	scalar	*Visual	NONE	<b>LIGHT</b>	---	---
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	---	---
Appearance	scalar	*Visual	NORML	<b>NORML</b>	---	---
Odor	scalar	*Visual	NORML	<b>NORML</b>	---	---
Emulsified Water	scalar	*Visual	>1.01	<b>NEG</b>	---	---

## FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m	>170	<b>10</b>	---	---
Boron	ppm	ASTM D5185m	400	<b>16</b>	---	---
Barium	ppm	ASTM D5185m	200	<b>0</b>	---	---
Molybdenum	ppm	ASTM D5185m	12	<b>0</b>	---	---
Manganese	ppm	ASTM D5185m		<b>5</b>	---	---
Magnesium	ppm	ASTM D5185m	12	<b>3</b>	---	---
Calcium	ppm	ASTM D5185m	150	<b>96</b>	---	---
Phosphorus	ppm	ASTM D5185m	1650	<b>2276</b>	---	---
Zinc	ppm	ASTM D5185m	125	<b>1531</b>	---	---
Sulfur	ppm	ASTM D5185m	22500	<b>40193</b>	---	---
Visc @ 40°C	cSt	ASTM D445	143	<b>216</b>	---	---



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : BE0024627  
**Lab Number** : 06083906  
**Unique Number** : 10871351  
**Test Package** : MOBCE  
**Received** : 08 Feb 2024  
**Tested** : 09 Feb 2024  
**Diagnosed** : 11 Feb 2024 - Don Baldrige

**National Equipment Dealers LLC NE**  
 215 Woodside Drive  
 Lexington, NC  
 US 27292  
 Contact: Steven Gawthrop  
 sgawthrop@nedealers.com  
 T:  
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.  
 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.  
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)