



# VOLVO

## OIL ANALYSIS REPORT

WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>



Area  
**TMR-Tampa Port**  
Machine Id  
**562178 VOLVO L180H 5499**  
Component  
**Transmission (Auto)**  
Fluid  
**VOLVO AT 102 (--- GAL)**

### RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>VCP429451</b>	DJJ0005156	VCP423597
Sample Date		Client Info		<b>24 Jan 2024</b>	11 Dec 2023	21 Mar 2023
Machine Age	hrs	Client Info		<b>11495</b>	11063	7773
Oil Age	hrs	Client Info		<b>0</b>	2000	773
Filter Age	hrs	Client Info		<b>0</b>	1000	0
Oil Changed		Client Info		<b>N/A</b>	Changed	Not Changd
Filter Changed		Client Info		<b>N/A</b>	Changed	Not Changd
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

### WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>160	<b>6</b>	20	13
Chromium	ppm	ASTM D5185m	>5	<b>&lt;1</b>	<1	0
Nickel	ppm	ASTM D5185m	>5	<b>0</b>	0	0
Titanium	ppm	ASTM D5185m		<b>0</b>	<1	0
Silver	ppm	ASTM D5185m	>5	<b>0</b>	0	0
Aluminum	ppm	ASTM D5185m	>50	<b>0</b>	1	<1
Lead	ppm	ASTM D5185m	>50	<b>0</b>	0	0
Copper	ppm	ASTM D5185m	>225	<b>0</b>	4	3
Tin	ppm	ASTM D5185m	>10	<b>0</b>	0	0
Vanadium	ppm	ASTM D5185m		<b>0</b>	<1	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

### CONTAMINATION










There is no indication of any contamination in the fluid.

Silicon	ppm	ASTM D5185m	>20	<b>&lt;1</b>	4	3
Potassium	ppm	ASTM D5185m	>20	<b>0</b>	1	0
Water		WC Method	>0.1	<b>NEG</b>	NEG	NEG
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	<b>NEG</b>	NEG	NEG

### FLUID CONDITION

The condition of the fluid is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		<b>&lt;1</b>	0	2
Boron	ppm	ASTM D5185m	187	<b>91</b>	93	98
Barium	ppm	ASTM D5185m	0.0	<b>&lt;1</b>	0	0
Molybdenum	ppm	ASTM D5185m	0.0	<b>0</b>	<1	<1
Manganese	ppm	ASTM D5185m	0.0	<b>&lt;1</b>	<1	<1
Magnesium	ppm	ASTM D5185m	6.8	<b>0</b>	2	<1
Calcium	ppm	ASTM D5185m	215	<b>56</b>	75	74
Phosphorus	ppm	ASTM D5185m	445	<b>196</b>	156	207
Zinc	ppm	ASTM D5185m	56	<b>2</b>	0	4
Sulfur	ppm	ASTM D5185m	1336	<b>1780</b>	2210	2349
Visc @ 40°C	cSt	ASTM D445	35.3	<b>28.4</b>	28.0	28.6



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : VCP429451  
**Lab Number** : 06084009  
**Unique Number** : 10871454  
**Test Package** : MOB 1

**Received** : 08 Feb 2024  
**Tested** : 09 Feb 2024  
**Diagnosed** : 11 Feb 2024 - Don Baldrige

**TRADEMARK METALS RECYCLING - TAMPA PORT**  
 4943 PORT SUTTON RD  
 TAMPA, FL  
 US 33619  
 Contact: RYAN BOWDEN

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:  
F: