
WEAR CONTAMINATION **FLUID CONDITION**


NORMAL NORMAL NORMAL


PIERCE TRUCK 222


Component Hydraulic System

{not provided} (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number	UOIVI	Client Info	LIIIII/ADII	WC0882453	WC0777584	WC0639756
Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Date		Client Info		19 Jan 2024	09 Feb 2023	14 Jan 2022
	Machine Age	mls	Client Info		116241	0	116241
	Oil Age	mls	Client Info		116241	0	116241
	Filter Age	mls	Client Info		0	0	116241
	Oil Changed		Client Info		N/A	Not Changd	N/A
	Filter Changed		Client Info		N/A	Not Changd	N/A
	Sample Status				NORMAL	NORMAL	NORMAL
WEAR							
WEAR	Iron	ppm	ASTM D5185m		0	<1	<1
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1	0	0
	Nickel	ppm	ASTM D5185m	>10	0	0	0
	Titanium	ppm	ASTM D5185m		0	0	0
	Silver	ppm	ASTM D5185m		0	0	0
	Aluminum	ppm	ASTM D5185m		0	<1	0
	Lead	ppm	ASTM D5185m		0	0	0
	Copper	ppm	ASTM D5185m		2	3	6
	Tin	ppm	ASTM D5185m	>10	0	0	0
	Vanadium	ppm	ASTM D5185m		0	0	0
	White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185m	>20	0	1	<1
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	0	0	0
	Water		WC Method	>0.1	NEG	NEG	NEG
	Silt	scalar	*Visual	NONE	NONE	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	Appearance	scalar	*Visual	NORML	NORML	NORML	NORM
	Odor	scalar	*Visual	NORML	NORML	NORML	NORM
	Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
FLUID CONDITION	Sodium	ppm	ASTM D5185m		0	<1	<1
	Boron	ppm	ASTM D5185m		0	0	1
The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185m		<1	0	0
	Molybdenum	ppm	ASTM D5185m		0	0	0
	Manganese	ppm	ASTM D5185m		<1	<1	0
	Magnesium	ppm	ASTM D5185m		0	1	0
	Calcium	ppm	ASTM D5185m		117	125	135
	Phosphorus	ppm	ASTM D5185m		668	585	673
	Zinc	ppm	ASTM D5185m		846	770	908
	Sulfur	ppm	ASTM D5185m		3837	3786	4196
	Visc @ 40°C	cSt	ASTM D445		62.5	62.4	62.9
Report Id: FORBRIAL IWUSCARI 06084074 (Generated: 02/09/2024 21:45:11) Rev: 1	_					tted Bv: RAN	













Laboratory Sample No.

Lab Number : 06084074 Unique Number : 10871519

: WC0882453

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 08 Feb 2024 **Tested** : 09 Feb 2024

> Diagnosed : 09 Feb 2024 - Wes Davis

Test Package : FLEET Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

FORESTDALE FIRE DEPT

751 HEFLIN EAST BIRMINGHAM, AL US 35214 Contact: LT PERRY

T: (205)791-0014 F: