



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
FSP137681 (S/N 3HAMMMMN2K1056817)

Component
Diesel Engine

Fluid
DIESEL ENGINE OIL SAE 15W40 (18 QTS)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0875765	WC0875816	WC0852283
Sample Date		Client Info		26 Jan 2024	14 Nov 2023	11 Sep 2023
Machine Age	mls	Client Info		156350	155030	151178
Oil Age	mls	Client Info		10000	0	0
Filter Age	mls	Client Info		0	0	0
Oil Changed		Client Info		Changed	N/A	Changed
Filter Changed		Client Info		N/A	N/A	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>80	6	7	24
Chromium	ppm	ASTM D5185m	>5	0	0	<1
Nickel	ppm	ASTM D5185m	>2	0	<1	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>3	0	<1	0
Aluminum	ppm	ASTM D5185m	>30	2	3	9
Lead	ppm	ASTM D5185m	>30	0	<1	0
Copper	ppm	ASTM D5185m	>150	<1	5	<1
Tin	ppm	ASTM D5185m	>5	<1	1	<1
Vanadium	ppm	ASTM D5185m		<1	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>20	4	3	6
Potassium	ppm	ASTM D5185m	>20	<1	4	4
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.1	0.3	0.3
Nitration	Abs/cm	*ASTM D7624	>20	5.7	8.0	8.3
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.4	19.4	19.4
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>158	1	1	3
Boron	ppm	ASTM D5185m	250	391	6	8
Barium	ppm	ASTM D5185m	10	0	0	<1
Molybdenum	ppm	ASTM D5185m	100	85	86	72
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m	450	454	913	1017
Calcium	ppm	ASTM D5185m	3000	1303	1052	1170
Phosphorus	ppm	ASTM D5185m	1150	1031	1040	1095
Zinc	ppm	ASTM D5185m	1350	1232	1218	1323
Sulfur	ppm	ASTM D5185m	4250	3316	3138	3896
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.7	15.3	15.8
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	7.8	7.7	8.6
Visc @ 100°C	cSt	ASTM D445	14.4	13.4	12.5	12.6



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : WC0875765

Lab Number : 06084192

Unique Number : 10871637

Test Package : FLEET

Received : 08 Feb 2024

Tested : 09 Feb 2024

Diagnosed : 09 Feb 2024 - Wes Davis

FRESHPOINT

8801 EXCHANGE DRIVE

ORLANDO, FL

US 32809

Contact: CRAIG EVANS

evans_craig@sbcglobal.net

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: