



TRAAP

Texas Refinery Advanced Analysis Program

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
VOLVO EC380EL E-27 (S/N 314740)

Component
Diesel Engine

Fluid
TRC MOLY XL PRO-SPEC III SYNTHETIC15W40 (52 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		TR06084354	TR06003774	TR05911424
Sample Date		Client Info		29 Jan 2024	04 Nov 2023	22 Jul 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		313	1057	572
Filter Age	hrs	Client Info		313	1057	572
Oil Changed		Client Info		Not Changd	Changed	Not Changd
Filter Changed		Client Info		Not Changd	Changed	Not Changd
Sample Status				NORMAL	ABNORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	7	23	11
Chromium	ppm	ASTM D5185m	>10	0	<1	<1
Nickel	ppm	ASTM D5185m	>10	0	<1	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>10	2	4	3
Lead	ppm	ASTM D5185m	>20	<1	4	0
Copper	ppm	ASTM D5185m	>15	<1	3	<1
Tin	ppm	ASTM D5185m	>10	<1	2	0
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>20	7	11	8
Potassium	ppm	ASTM D5185m	>20	<1	1	0
Fuel		WC Method	>6.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.1	0.2	0.1
Nitration	Abs/cm	*ASTM D7624	>20	12.0	26.9	17.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.9	44.6	32.5
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		4	8	7
Boron	ppm	ASTM D5185m		47	126	132
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		132	210	210
Manganese	ppm	ASTM D5185m		<1	1	<1
Magnesium	ppm	ASTM D5185m		137	543	539
Calcium	ppm	ASTM D5185m	4500	3935	4702	4572
Phosphorus	ppm	ASTM D5185m		921	1081	1055
Zinc	ppm	ASTM D5185m	1400	1036	1324	1233
Sulfur	ppm	ASTM D5185m		4050	4266	4949
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.4	55.6	30.6
Base Number (BN)	mg KOH/g	ASTM D2896	15	11.90	9.54	15.04
Visc @ 100°C	cSt	ASTM D445	15.5	14.6	▲ 20.64	16.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : TR06084354
Lab Number : 06084354
Unique Number : 10871799
Test Package : MOB 2

Received : 08 Feb 2024
Tested : 09 Feb 2024
Diagnosed : 09 Feb 2024 - Wes Davis

NUTTER ENTERPRISES INC
 28 STONE RD
 BELMONT, NH
 US 03220
 Contact: DON PERCY

To discuss this sample report, contact Customer Service at 1-800-827-0711.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: