



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	ABNORMAL

Machine Id
JOHN DEERE 350G 1FF350GXCLF814435

Component
Hydraulic System

Fluid
HITACHI HYDRAULIC SUPER EX 46HN (--- GAL)

RECOMMENDATION

Recommend drain oil if not already done. Reduce drain interval to 2000 hours or drain and flush and use recommended zinc free oil.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0202856	JR0181368	JR0163857
Sample Date		Client Info		08 Feb 2024	03 Aug 2023	23 Mar 2023
Machine Age	hrs	Client Info		5523	4570	4039
Oil Age	hrs	Client Info		5523	4570	4039
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Chngd	Not Chngd	Not Chngd
Filter Changed		Client Info		Not Chngd	Not Chngd	Changed
Sample Status				ABNORMAL	NORMAL	ABNORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184	>50	12	10	8
Iron	ppm	ASTM D5185m	>32	6	<1	8
Chromium	ppm	ASTM D5185m	>9	<1	0	<1
Nickel	ppm	ASTM D5185m	>5	0	0	0
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>9	<1	<1	3
Lead	ppm	ASTM D5185m	>28	0	0	0
Copper	ppm	ASTM D5185m	>50	11	0	5
Tin	ppm	ASTM D5185m	>5	0	0	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

Silicon	ppm	ASTM D5185m	>11	3	1	4
Potassium	ppm	ASTM D5185m	>20	0	0	<1
Water		WC Method	>0.075	NEG	NEG	NEG
Particles >4µm		ASTM D7647	>80000	5156	6820	6858
Particles >6µm		ASTM D7647	>20000	798	1486	618
Particles >14µm		ASTM D7647	>640	104	62	18
Particles >21µm		ASTM D7647	>160	40	8	2
Particles >38µm		ASTM D7647	>40	6	0	0
Particles >71µm		ASTM D7647	>10	1	0	0
Oil Cleanliness		ISO 4406 (c)	>23/21/16	20/17/14	20/18/13	20/16/11
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

Zinc level above manufacturer's recommendations. The AN level is acceptable for this fluid.

Sodium	ppm	ASTM D5185m	>21	1	0	<1
Boron	ppm	ASTM D5185m		3	0	<1
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		2	<1	1
Manganese	ppm	ASTM D5185m		0	0	<1
Magnesium	ppm	ASTM D5185m		12	2	9
Calcium	ppm	ASTM D5185m		132	145	811
Phosphorus	ppm	ASTM D5185m	827	476	652	568
Zinc	ppm	ASTM D5185m	0	▲ 124	60	▲ 393
Sulfur	ppm	ASTM D5185m	13	447	349	2262
Acid Number (AN)	mg KOH/g	ASTM D8045	0.06	0.405	0.15	0.85
Visc @ 40°C	cSt	ASTM D445	47	46.9	48.0	40.6



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0202856 **Received** : 09 Feb 2024
Lab Number : 06084684 **Tested** : 12 Feb 2024
Unique Number : 10872129 **Diagnosed** : 12 Feb 2024 - Jonathan Hester
Test Package : CONST (Additional Tests: PQ)

JRE - GARNER
 4161 AUBURN CHURCH RD
 GARNER, NC
 US 27529
 Contact: RALEIGH SHOP
 sean.betts@jamesriverequipment.com; catherine.anastasio@wearcheck.com
 T: (919)614-2260
 F: (919)779-5432

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)