



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
JOHN DEERE 650K 1T0650KXCEE268735
 Component
Hydraulic System
 Fluid
JOHN DEERE HYDRAU (15 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0191359	JR0176958	JR0149599
Sample Date		Client Info		31 Jan 2024	27 Jul 2023	02 Nov 2022
Machine Age	hrs	Client Info		6533	6090	5518
Oil Age	hrs	Client Info		443	1995	1423
Filter Age	hrs	Client Info		443	1995	1423
Oil Changed		Client Info		Not Chngd	Changed	Not Chngd
Filter Changed		Client Info		Not Chngd	Changed	Not Chngd
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184	>50	17	27	19
Iron	ppm	ASTM D5185m	>23	12	25	22
Chromium	ppm	ASTM D5185m	>9	5	6	3
Nickel	ppm	ASTM D5185m	>5	0	0	0
Titanium	ppm	ASTM D5185m		0	<1	<1
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>9	2	6	5
Lead	ppm	ASTM D5185m	>28	0	0	0
Copper	ppm	ASTM D5185m	>51	11	24	22
Tin	ppm	ASTM D5185m	>5	0	<1	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	LIGHT	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Silicon	ppm	ASTM D5185m	>31	4	8	6
Potassium	ppm	ASTM D5185m	>20	0	1	0
Water		WC Method	>0.075	NEG	NEG	NEG
Particles >4µm		ASTM D7647	>80000	3036	6924	18368
Particles >6µm		ASTM D7647	>20000	340	266	2059
Particles >14µm		ASTM D7647	>640	21	12	241
Particles >21µm		ASTM D7647	>160	5	3	68
Particles >38µm		ASTM D7647	>40	0	0	2
Particles >71µm		ASTM D7647	>10	0	0	0
Oil Cleanliness		ISO 4406 (c)	>23/21/16	19/16/12	20/15/11	21/18/15
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	LIGHT
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>21	<1	2	0
Boron	ppm	ASTM D5185m		8	26	25
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		8	23	25
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		29	82	81
Calcium	ppm	ASTM D5185m	87	166	260	271
Phosphorus	ppm	ASTM D5185m	727	644	667	653
Zinc	ppm	ASTM D5185m	900	815	842	819
Sulfur	ppm	ASTM D5185m	1500	1644	2110	2125
Acid Number (AN)	mg KOH/g	ASTM D8045	1.0	0.63	0.75	0.79
Visc @ 40°C	cSt	ASTM D445	65	58.8	58.7	59.1



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0191359 **Received** : 09 Feb 2024
Lab Number : 06084695 **Tested** : 12 Feb 2024
Unique Number : 10872140 **Diagnosed** : 12 Feb 2024 - Wes Davis
Test Package : CONST (Additional Tests: PQ)

TENNOCA CONSTRUCTION
 PO BOX 2379
 CANDLER, NC
 US 28715
 Contact: MARK ROSS
 mark@tennoca.com
 T: (828)665-8331
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)