WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL

[RS036848]

KOBELCO SK500LC-10 Y514605002

Component Rear Left Final Drive

| Resample at the next service interval to monitor. | Test | UOM | Method | Limit/Abn | Current | History1 | History2 |
|--|------------------|--------|----------------------------|-----------|-------------|----------|----------|
| | Sample Number | | Client Info | | VCP430559 | | |
| | Sample Date | | Client Info | | 26 Jan 2024 | | |
| | Machine Age | hrs | Client Info | | 3629 | | |
| | Oil Age | hrs | Client Info | | 0 | | |
| | Filter Age | hrs | Client Info | | 0 | | |
| | Oil Changed | | Client Info | | Changed | | |
| | Filter Changed | | Client Info | | Not Changd | | |
| | Sample Status | | | | NORMAL | | |
| VEAR | Iron | nnm | ACTM DE10Em | - 500 | 0.4 | | |
| All component wear rates are normal. | Iron Chromium | ppm | ASTM D5185m ASTM D5185m | | 84 2 | | |
| | Nickel | ppm | ASTM D5185m | | <1 | | |
| | Titanium | ppm | ASTM D5185m | >10 | <1 | | |
| | Silver | ppm | ASTM D5185m | | 0 | | |
| | Aluminum | ppm | ASTM D5185m | >25 | <1 | | |
| | Lead | ppm | ASTM D5185m | | <1 | | |
| | Copper | ppm | ASTM D5185m | | <1 | | |
| | Tin | ppm | ASTM D5185m | | <1 | | |
| | Vanadium | ppm | ASTM D5185m | 7.0 | 0 | | |
| | White Metal | scalar | *Visual | NONE | NONE | | |
| | Yellow Metal | scalar | *Visual | NONE | NONE | | |
| | | | | | | | |
| CONTAMINATION | Silicon | ppm | ASTM D5185m | >75 | 13 | | |
| There is no indication of any contamination in the oil. | Potassium | ppm | ASTM D5185m | | <1 | | |
| | Water | | WC Method | >0.2 | NEG | | |
| | Silt | scalar | *Visual | NONE | NONE | | |
| | Debris | scalar | *Visual | NONE | NONE | | |
| | Sand/Dirt | scalar | *Visual | NONE | NONE | | |
| | Appearance | scalar | *Visual | NORML | NORML | | |
| | Odor | scalar | *Visual | NORML | NORML | | |
| | Emulsified Water | scalar | *Visual | >0.2 | NEG | | |
| LUID CONDITION | Sodium | ppm | ASTM D5185m | | 0 | | |
| Confirm oil type. The condition of the oil is acceptable for the time in | Boron | ppm | ASTM D5185m | 400 | 188 | | |
| service. | Barium | ppm | ASTM D5185m | 200 | 0 | | |
| | Molybdenum | ppm | ASTM D5185m | 12 | <1 | | |
| | Manganese | ppm | ASTM D5185m | | 2 | | |
| | Magnesium | ppm | ASTM D5185m | 12 | 1 | | |
| | Calcium | ppm | ASTM D5185m | 150 | 4 | | |
| | Phosphorus | ppm | ASTM D5185m | 1650 | 1025 | | |
| | Zinc | ppm | ASTM D5185m | 125 | 3 | | |
| | Sulfur | ppm | ASTM D5185m | 22500 | 23653 | | |
| | Visc @ 40°C | cSt | ASTM D445 | 368 | 148 | | |
| | _ | | | | \ | | |







Certificate L2367

Laboratory Sample No.

Lab Number : 06085078 Unique Number : 10872523 Test Package : MOB 1

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : VCP430559 : 09 Feb 2024 **Tested** : 11 Feb 2024

: 12 Feb 2024 - Don Baldridge Diagnosed

COWIN EQUIPMENT COMPANY

P.O. DRAWER 9367 MONTGOMERY, AL US 36108

Contact: BRYAN DICKS

bdicks@cowin.com T: (334)262-6642 F: (334)269-1514

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)