



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
95055
Component
Diesel Engine
Fluid
AMERIGUARD 15W40 (10 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		SBP0005541	SBP0001646	SBP0000760
Sample Date		Client Info		21 Jan 2024	01 Mar 2023	25 Feb 2022
Machine Age	mls	Client Info		110864	98360	84086
Oil Age	mls	Client Info		12504	14274	11682
Filter Age	mls	Client Info		12504	14274	11682
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>80	34	50	32
Chromium	ppm	ASTM D5185m	>5	2	2	1
Nickel	ppm	ASTM D5185m	>2	1	<1	0
Titanium	ppm	ASTM D5185m		<1	0	<1
Silver	ppm	ASTM D5185m	>3	0	0	<1
Aluminum	ppm	ASTM D5185m	>30	4	8	7
Lead	ppm	ASTM D5185m	>30	1	0	0
Copper	ppm	ASTM D5185m	>150	5	6	6
Tin	ppm	ASTM D5185m	>5	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>20	6	5	6
Potassium	ppm	ASTM D5185m	>20	6	10	9
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.4	0.6	0.6
Nitration	Abs/cm	*ASTM D7624	>20	10.7	12.2	13.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.3	23.0	25.1
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<1	6	6
Boron	ppm	ASTM D5185m		2	8	40
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		68	57	25
Manganese	ppm	ASTM D5185m		<1	1	<1
Magnesium	ppm	ASTM D5185m		1055	918	642
Calcium	ppm	ASTM D5185m		1181	1177	1676
Phosphorus	ppm	ASTM D5185m		1015	936	730
Zinc	ppm	ASTM D5185m		1347	1228	858
Sulfur	ppm	ASTM D5185m		3166	3631	2437
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.6	21.0	24.8
Base Number (BN)	mg KOH/g	ASTM D2896		6.9	6.4	7.7
Visc @ 100°C	cSt	ASTM D445		13.4	13.1	13.5



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : SBP0005541
Lab Number : 06085276
Unique Number : 10872721
Test Package : FLEET

Received : 09 Feb 2024
Tested : 12 Feb 2024
Diagnosed : 12 Feb 2024 - Wes Davis

Sapp Bros. Fleet - Julesburg Location

US
 Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
 F: