



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
29M
Component
Gasoline Engine
Fluid
MOBIL 1 5W30 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0100925	GFL0086810	GFL0086871
Sample Date		Client Info		06 Feb 2024	28 Nov 2023	08 Sep 2023
Machine Age	mls	Client Info		280516	280516	265994
Oil Age	mls	Client Info		265994	280516	265994
Filter Age	mls	Client Info		0	280516	0
Oil Changed		Client Info		Not Changd	Not Changd	N/A
Filter Changed		Client Info		Not Changd	Not Changd	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>150	31	23	28
Chromium	ppm	ASTM D5185m	>20	1	1	1
Nickel	ppm	ASTM D5185m	>5	<1	1	1
Titanium	ppm	ASTM D5185m		5	6	4
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>40	15	17	15
Lead	ppm	ASTM D5185m	>50	0	0	0
Copper	ppm	ASTM D5185m	>155	3	3	4
Tin	ppm	ASTM D5185m	>10	0	<1	<1
Vanadium	ppm	ASTM D5185m		0	<1	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>30	22	23	28
Potassium	ppm	ASTM D5185m	>20	1	0	<1
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844		0.1	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>20	13.8	12.6	11.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	24.0	23.6	23.1
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>400	5	4	4
Boron	ppm	ASTM D5185m	94	30	31	25
Barium	ppm	ASTM D5185m	0.0	0	<1	0
Molybdenum	ppm	ASTM D5185m	0.0	220	205	252
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m	1388	562	540	582
Calcium	ppm	ASTM D5185m	820	1305	1214	1379
Phosphorus	ppm	ASTM D5185m	720	718	679	716
Zinc	ppm	ASTM D5185m	780	923	802	867
Sulfur	ppm	ASTM D5185m	2240	2154	1982	2523
Oxidation	Abs/.1mm	*ASTM D7414	>25	20.4	18.6	18.3
Base Number (BN)	mg KOH/g	ASTM D2896		4.5	3.5	3.8
Visc @ 100°C	cSt	ASTM D445	11.3	10.4	10.8	10.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0100925
Lab Number : 06085598
Unique Number : 10873043
Test Package : FLEET

GFL Environmental - 419 - Metro Saginaw
 6950 N Michigan
 Saginaw, MI
 US 48604

Contact: Jeremy Hines
 jhines@gflenv.com

T: (800)684-1277

F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)