



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
923040-260203

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0088134	GFL0088215	GFL0088212
Sample Date		Client Info		29 Jan 2024	18 Dec 2023	09 Nov 2023
Machine Age	mls	Client Info		14894	0	11999
Oil Age	mls	Client Info		0	0	0
Filter Age	mls	Client Info		0	0	0
Oil Changed		Client Info		Changed	N/A	Not Changed
Filter Changed		Client Info		Changed	N/A	Changed
Sample Status				NORMAL	ATTENTION	ATTENTION

WEAR

Metal levels are typical for a new component breaking in.

Iron	ppm	ASTM D5185m	>100	13	66	50
Chromium	ppm	ASTM D5185m	>20	0	2	1
Nickel	ppm	ASTM D5185m	>4	0	<1	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	1	5	4
Lead	ppm	ASTM D5185m	>40	0	2	<1
Copper	ppm	ASTM D5185m	>330	1	7	4
Tin	ppm	ASTM D5185m	>15	0	0	0
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	4	13	12
Potassium	ppm	ASTM D5185m	>20	0	<1	<1
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.3	1.3	1
Nitration	Abs/cm	*ASTM D7624	>20	5.9	10.6	9.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.1	22.6	21.0
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		4	22	13
Boron	ppm	ASTM D5185m	0	0	4	5
Barium	ppm	ASTM D5185m	0	0	0	5
Molybdenum	ppm	ASTM D5185m	60	60	58	61
Manganese	ppm	ASTM D5185m	0	<1	4	3
Magnesium	ppm	ASTM D5185m	1010	942	885	1016
Calcium	ppm	ASTM D5185m	1070	1074	1026	1209
Phosphorus	ppm	ASTM D5185m	1150	1050	868	1156
Zinc	ppm	ASTM D5185m	1270	1299	1193	1487
Sulfur	ppm	ASTM D5185m	2060	3154	2801	3502
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.3	19.6	17.4
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	9.0	6.4	8.2
Visc @ 100°C	cSt	ASTM D445	15.4	13.3	▲ 10.8	▲ 10.9



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0088134
Lab Number : 06085627
Unique Number : 10873072
Test Package : FLEET

Received : 12 Feb 2024
Tested : 12 Feb 2024
Diagnosed : 12 Feb 2024 - Wes Davis

GFL Environmental - 820 - Joplin Hauling
 3700 West 7th Street
 Joplin, MO
 US 64801
 Contact: James Jarrett
 jjarrett@gflenv.com
 T: (417)310-2802
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)