



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
229033

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (--- LTR)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0107001	GFL0094250	GFL0085386
Sample Date		Client Info		07 Feb 2024	02 Nov 2023	21 Jul 2023
Machine Age	mls	Client Info		278625	12816	6587
Oil Age	mls	Client Info		278625	0	6587
Filter Age	mls	Client Info		278625	0	6587
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	20	6	12
Chromium	ppm	ASTM D5185m	>20	0	<1	<1
Nickel	ppm	ASTM D5185m	>4	0	<1	0
Titanium	ppm	ASTM D5185m		0	<1	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	<1	2	<1
Lead	ppm	ASTM D5185m	>40	0	1	2
Copper	ppm	ASTM D5185m	>330	0	<1	<1
Tin	ppm	ASTM D5185m	>15	0	0	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	2	3	0
Potassium	ppm	ASTM D5185m	>20	6	2	<1
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	1.5	1	1.9
Nitration	Abs/cm	*ASTM D7624	>20	10.2	7.2	10.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.8	19.8	23.2
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		16	0	0
Boron	ppm	ASTM D5185m	0	<1	2	5
Barium	ppm	ASTM D5185m	0	0	5	2
Molybdenum	ppm	ASTM D5185m	60	56	61	68
Manganese	ppm	ASTM D5185m	0	0	<1	<1
Magnesium	ppm	ASTM D5185m	1010	889	863	849
Calcium	ppm	ASTM D5185m	1070	1077	1084	1268
Phosphorus	ppm	ASTM D5185m	1150	999	1029	1026
Zinc	ppm	ASTM D5185m	1270	1199	1193	1240
Sulfur	ppm	ASTM D5185m	2060	2964	2905	3209
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.6	14.9	18.4
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.6	8.9	8.9
Visc @ 100°C	cSt	ASTM D445	15.4	12.7	14.2	14.5



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0107001
Lab Number : 06085654
Unique Number : 10873099
Test Package : FLEET

Received : 12 Feb 2024
Tested : 12 Feb 2024
Diagnosed : 12 Feb 2024 - Wes Davis

GFL Environmental - 882 - Gainesville
 5002 SW 41st Blvd
 Gainesville, FL
 US 32608
 Contact: ROBERT CLARK
 robert.clark@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: