



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>



Machine Id  
**912019**  
Component  
**Diesel Engine**  
Fluid  
**PETRO CANADA DURON SHP 15W40 (36 QTS)**

**RECOMMENDATION**

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>GFL0110035</b>	GFL0059270	GFL0059140
Sample Date		Client Info		<b>07 Feb 2024</b>	15 Nov 2023	07 Nov 2023
Machine Age	hrs	Client Info		<b>3604</b>	3601	3601
Oil Age	hrs	Client Info		<b>600</b>	3601	0
Filter Age	hrs	Client Info		<b>600</b>	3601	0
Oil Changed		Client Info		<b>Changed</b>	N/A	Changed
Filter Changed		Client Info		<b>Changed</b>	N/A	Changed
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

**WEAR**

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>120	<b>20</b>	60	25
Chromium	ppm	ASTM D5185m	>20	<b>&lt;1</b>	2	3
Nickel	ppm	ASTM D5185m	>5	<b>0</b>	5	<1
Titanium	ppm	ASTM D5185m	>2	<b>0</b>	0	<1
Silver	ppm	ASTM D5185m	>2	<b>0</b>	<1	<1
Aluminum	ppm	ASTM D5185m	>20	<b>12</b>	2	31
Lead	ppm	ASTM D5185m	>40	<b>0</b>	<1	<1
Copper	ppm	ASTM D5185m	>330	<b>&lt;1</b>	13	7
Tin	ppm	ASTM D5185m	>15	<b>0</b>	2	<1
Vanadium	ppm	ASTM D5185m		<b>0</b>	0	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

**CONTAMINATION**







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	<b>3</b>	7	10
Potassium	ppm	ASTM D5185m	>20	<b>0</b>	1	59
Fuel		WC Method	>3.0	<b>&lt;1.0</b>	<1.0	<1.0
Water		WC Method	>0.2	<b>NEG</b>	NEG	NEG
Glycol		WC Method		<b>NEG</b>	NEG	NEG
Soot %	%	*ASTM D7844	>4	<b>0.8</b>	1.3	0.7
Nitration	Abs/cm	*ASTM D7624	>20	<b>8.1</b>	11.1	7.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>19.3</b>	23.5	19.3
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	<b>NEG</b>	NEG	NEG

**FLUID CONDITION**

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>4</b>	5	42
Boron	ppm	ASTM D5185m	0	<b>2</b>	3	<1
Barium	ppm	ASTM D5185m	0	<b>0</b>	0	6
Molybdenum	ppm	ASTM D5185m	60	<b>55</b>	63	62
Manganese	ppm	ASTM D5185m	0	<b>&lt;1</b>	1	<1
Magnesium	ppm	ASTM D5185m	1010	<b>894</b>	947	883
Calcium	ppm	ASTM D5185m	1070	<b>975</b>	1078	1082
Phosphorus	ppm	ASTM D5185m	1150	<b>1042</b>	1017	988
Zinc	ppm	ASTM D5185m	1270	<b>1206</b>	1292	1177
Sulfur	ppm	ASTM D5185m	2060	<b>2891</b>	2219	3346
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>15.0</b>	21.8	14.5
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	<b>8.8</b>	4.7	8.6
Visc @ 100°C	cSt	ASTM D445	15.4	<b>13.6</b>	13.6	14.5



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : GFL0110035  
**Lab Number** : 06085770  
**Unique Number** : 10873215  
**Test Package** : FLEET

**Received** : 12 Feb 2024  
**Tested** : 13 Feb 2024  
**Diagnosed** : 13 Feb 2024 - Wes Davis

**GFL Environmental - 410 - Michigan West**  
 39000 Van Born Rd  
 Wayne, MI  
 US 48184

Contact: Belal Dgheish  
 bdgheish@gflenv.com

T: (734)714-2340

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: