


## Machine Id 8013505 Component Diesel Engine Fluid {not provided} (---- GAL)


RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		IL0034843		
	Sample Date		Client Info		11 Feb 2024		
	Machine Age	mls	Client Info		0		
	Oil Age	mls	Client Info		0		
	Filter Age	mls	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR All component wear rates are normal.	Iron		ASTM D5185m	. 100	40		
		ppm			48		
	Chromium	ppm	ASTM D5185m		4		
	Nickel	ppm	ASTM D5185m	>4	0		
	Titanium	ppm	ASTM D5185m	-	<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		5		
	Lead	ppm	ASTM D5185m		1		
	Copper	ppm	ASTM D5185m		49		
	Tin	ppm	ASTM D5185m	>15	<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>25	17		
OUTAMINATION	Potassium	ppm	ASTM D5185m		2		
There is no indication of any contamination in the oil.	Fuel	%	ASTM D3103ml		<1.0		
	Water	70	WC Method		NEG		
	Glycol		WC Method	20.2	NEG		
	Soot %	%	*ASTM D7844	<u>.</u> ?	1.4		
	Nitration	Abs/cm	*ASTM D7624	>20	12.4		
	Sulfation	Abs/.1mm	*ASTM D7024		25.2		
	Silt			NONE	NONE		
	Debris	scalar	*Visual		NONE		
		scalar	*Visual	NONE			
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		4		
	Boron	ppm	ASTM D5185m		19		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		48		
	Manganese	ppm	ASTM D5185m		1		
	Magnesium	ppm	ASTM D5185m		529		
	Calcium	ppm	ASTM D5185m		1732		
	Phosphorus	ppm	ASTM D5185m		739		
	Zinc	ppm	ASTM D5185m		914		
	Sulfur	ppm	ASTM D5185m		2046		
	Oxidation	Abs/.1mm	*ASTM D7414	>25	25.9		
	Base Number (BN)			- 20	7.1		
					10.0		

Visc @ 100°C cSt

ASTM D445

12.0





Feb11/24 **IDEALEASE OF ATLANTA - FULTON** Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. Received 4675 BAKERS FERRY ROAD : IL0034843 : 12 Feb 2024 Lab Number : 06085896 Tested : 13 Feb 2024 ATLANTA, GA Diagnosed Unique Number : 10873341 : 13 Feb 2024 - Don Baldridge US 30331 Test Package : FLEET (Additional Tests: FuelDilution) Contact: DAVID JOHNS Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. davidjohns@idealease.com \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (404)699-5571 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (404)699-7420

Contact/Location: DAVID JOHNS - IDEATLGA