
WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL

JOHN DEERE 768L-II 1DW768LBCMF712062

Component Bogie/Center Right Tandem

	T4	11044	N / a d la I	Line D. / A.L.	(I Bakanna	I Batan o
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		JR0161249 09 Feb 2024	JR0110313	
	Sample Date	hro	Client Info			12 Jan 2022	
	Machine Age Oil Age	hrs	Client Info		4470	502 502	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed	1115	Client Info		Changed	Changed	
	Filter Changed		Client Info		Changed	N/A	
	Sample Status		Olichi illio		NORMAL	NORMAL	
A/CAD							
WEAR	PQ		ASTM D8184	0.50	15	32	
All component wear rates are normal.	Iron	ppm	ASTM D5185m		4	16	
	Chromium	ppm	ASTM D5185m		0	1	
	Nickel	ppm	ASTM D5185m	>5	0	0	
	Titanium	ppm	ASTM D5185m		0	0	
	Silver	ppm	ASTM D5185m	40	0	0	
	Aluminum	ppm	ASTM D5185m		0	<1	
	Lead	ppm	ASTM D5185m		0	0	
	Copper	ppm	ASTM D5185m	>25	0	0	
	Tin	ppm	ASTM D5185m		0	0	
	Vanadium	ppm	ASTM D5185m	NONE	0 NONE	0	
	White Metal	scalar	*Visual	NONE	NONE	LIGHT	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION	Silicon	ppm	ASTM D5185m	>100	3	3	
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	0	0	
	Water		WC Method	>0.1	NEG	NEG	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	LIGHT	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>21	0	1	
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		2	500	
	Barium	ppm	ASTM D5185m		0	0	
	Molybdenum	ppm	ASTM D5185m		0	<1	
	Manganese	ppm	ASTM D5185m		0	1	
	Magnesium	ppm	ASTM D5185m		8	793	
	Calcium	ppm	ASTM D5185m		56	28	
	Phosphorus	ppm	ASTM D5185m		305	1307	
	Zinc	ppm	ASTM D5185m		19	6	
	Sulfur	ppm	ASTM D5185m		18758	23343	
	Visc @ 40°C	cSt	ASTM D445		141	150	





Laboratory Sample No. Unique Number: 10873696

Lab Number : 06086251

: JR0161249

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received

: 12 Feb 2024 **Tested** Diagnosed Test Package : CONST (Additional Tests: PQ)

: 13 Feb 2024 : 13 Feb 2024 - Sean Felton

JRE - MOUNT GILEAD 305 NORTH MAIN STREET MOUNT GILEAD, NC

US 27306

Contact: ADAM CRUMP adam.crump@jamesriverequipment.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (910)439-4568