
WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL

JOHN DEERE 244L 1LU244LXKZB069718

Component Front Differential

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample. Test UOM Method Limit/Abn Current JR0195618 Sample Number Sample Date Client Info 09 Feb 2024 Machine Age hrs Client Info Oil Age hrs Client Info Oil Age Nor Client Info Oil Age Oil Age Nor Client Info Oil Age	History2
brand, type, and viscosity of the oil on your next sample. Sample Date Client Info O9 Feb 2024 Machine Age hrs Client Info 40	
brand, type, and viscosity of the oil on your next sample. Sample Date Client Info 09 Feb 2024 Machine Age hrs Client Info 40	
g l	
Oil Age hrs Client Info	
Oil Age hrs Client Info 0	
Filter Age hrs Client Info 0	
Oil Changed Client Info Not Changd	
Filter Changed Client Info N/A	
Sample Status NORMAL	
WEAR PQ ASTM D8184 281	
All component wear rates are normal. Iron ppm ASTM D5185m >500 180	
Chromium ppm ASTM D5185m >10 2	
Nickel ppm ASTM D5185m >10 0	
Titanium ppm ASTM D5185m 0	
Silver ppm ASTM D5185m 0	
Aluminum ppm ASTM D5185m >25 2	
LeadppmASTM D5185m>250	
Copper ppm ASTM D5185m >100 <1	
Tin ppm ASTM D5185m >10 0	
Vanadium ppm ASTM D5185m 0	
White Metal scalar *Visual NONE NONE	
Yellow Metal scalar *Visual NONE NONE	
CONTAMINATION Silicon ppm ASTM D5185m >75 20	
There is no indication of any contamination in the oil. Potassium ppm ASTM D5185m >20 <1	
Water WC Method >.2 NEG	
Silt scalar *Visual NONE NONE	
Debris scalar *Visual NONE NONE	
Sand/Dirt scalar *Visual NONE NONE	
Appearance scalar *Visual NORML	
Odor scalar *Visual NORML	
Emulsified Water scalar *Visual >.2 NEG	
FLUID CONDITION Sodium ppm ASTM D5185m 4	
The condition of the oil is acceptable for the time in service. Boron ppm ASTM D5185m 127	
Barium ppm ASTM D5185m 5	
Molybdenum ppm ASTM D5185m 11	
Manganese ppm ASTM D5185m 6	
MagnesiumppmASTM D5185m1	
Calcium ppm ASTM D5185m 815	
Phosphorus ppm ASTM D5185m 690	
Zinc ppm ASTM D5185m 1544	
Sulfur ppm ASTM D5185m 5062	
Visc @ 40°C cSt ASTM D445 104 Report Id: IAMWIN IWUSCARI 06086264 (Generated: 02/13/2024 10:51:16) Rev. 1	





Laboratory Sample No.

: JR0195618 Lab Number : 06086264 Unique Number : 10873709

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received

Tested Diagnosed Test Package : CONST (Additional Tests: PQ)

: 12 Feb 2024 : 13 Feb 2024 : 13 Feb 2024 - Wes Davis

JRE - STEPHENSON 245 YARDMASTER COURT STEPHENSON, VA US 22656-1761

Contact: PHIL DAUGHERTY pdaugherty@jamesriverequipment.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

F: (540)693-2588 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: PHIL DAUGHERTY - JAMWIN

T: x: