
**WEAR** CONTAMINATION **FLUID CONDITION** 

**NORMAL NORMAL ATTENTION** 

## **JOHN DEERE 244L 1LU244LXKZB069718**

Component Rear Right Final Drive

JOHN DEERE HY-GARD HYD/TRANS ( GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		JR0195569		
	Sample Date		Client Info		09 Feb 2024		
	Machine Age	hrs	Client Info		40		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		N/A		
	Sample Status				ATTENTION		
WEAR	PQ		ASTM D8184	>1250	31		
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>750	56		
	Chromium	ppm	ASTM D5185m	>9	<1		
	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>40	0		
	Lead	ppm	ASTM D5185m	>15	0		
	Copper	ppm	ASTM D5185m	>40	14		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION  There is no indication of any contamination in the oil.	Silicon	ppm	ASTM D5185m	>75	30		
	Potassium	ppm	ASTM D5185m	>20	0		
	Water		WC Method	>0.075	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.075	NEG		
FLUID CONDITION  The oil viscosity is higher than normal. This plus the additive levels indicates the addition of a different brand, or type of oil. Confirm oil type.	Sodium	ppm	ASTM D5185m	>51	3		
	Boron	ppm	ASTM D5185m	6	<b>128</b>		
	Barium	ppm	ASTM D5185m	0	7		
	Molybdenum	ppm	ASTM D5185m	0	0		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m	145	<b>2</b>		
	Calcium	ppm	ASTM D5185m		<b>799</b>		
	Phosphorus	ppm	ASTM D5185m	1290	<b>▲</b> 663		
	Zinc	ppm	ASTM D5185m	1640	1548		
	Sulfur	ppm	ASTM D5185m		4360		
	Visc @ 40°C	cSt	ASTM D445	57.0	▲ 80.2		





Laboratory Sample No.

Lab Number : 06086265 Unique Number : 10873710

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : JR0195569

Test Package : CONST ( Additional Tests: PQ )

: 12 Feb 2024 Received Tested Diagnosed

: 13 Feb 2024 : 13 Feb 2024 - Sean Felton

JRE - STEPHENSON 245 YARDMASTER COURT STEPHENSON, VA US 22656-1761

Contact: PHIL DAUGHERTY

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. pdaugherty@jamesriverequipment.com T: x:

Contact/Location: PHIL DAUGHERTY - JAMWIN

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (540)693-2588