
**WEAR CONTAMINATION FLUID CONDITION** 

**NORMAL NORMAL ATTENTION** 

## **JOHN DEERE 244L 1LU244LXKZB069718**

Component Front Left Final Drive

| JOHN DEERE HY-GARD HYD/TRANS ( GAL)  |                  |        |             |           |              |          |          |
|--|------------------|--------|-------------|-----------|--------------|----------|----------|
| RECOMMENDATION   | Test             | UOM    | Method      | Limit/Abn | Current      | History1 | History2 |
| Resample at the next service interval to monitor.  | Sample Number    |        | Client Info |           | JR0195617    |          |          |
|  | Sample Date      |        | Client Info |           | 09 Feb 2024  |          |          |
|  | Machine Age      | hrs    | Client Info |           | 40           |          |          |
|  | Oil Age          | hrs    | Client Info |           | 0            |          |          |
|  | Filter Age       | hrs    | Client Info |           | 0            |          |          |
|  | Oil Changed      |        | Client Info |           | Not Changd   |          |          |
|  | Filter Changed   |        | Client Info |           | N/A          |          |          |
|  | Sample Status    |        |             |           | ATTENTION    |          |          |
| WEAR   | PQ               |        | ASTM D8184  | >1250     | 40           |          |          |
| All component wear rates are normal.   | Iron             | ppm    | ASTM D5185m | >750      | 69           |          |          |
|  | Chromium         | ppm    | ASTM D5185m | >9        | 1            |          |          |
|  | Nickel           | ppm    | ASTM D5185m | >10       | 0            |          |          |
|  | Titanium         | ppm    | ASTM D5185m |           | 0            |          |          |
|  | Silver           | ppm    | ASTM D5185m |           | 0            |          |          |
|  | Aluminum         | ppm    | ASTM D5185m | >40       | 0            |          |          |
|  | Lead             | ppm    | ASTM D5185m | >15       | 0            |          |          |
|  | Copper           | ppm    | ASTM D5185m | >40       | 0            |          |          |
|  | Tin              | ppm    | ASTM D5185m | >10       | 0            |          |          |
|  | Vanadium         | ppm    | ASTM D5185m |           | 0            |          |          |
|  | White Metal      | scalar | *Visual     | NONE      | NONE         |          |          |
|  | Yellow Metal     | scalar | *Visual     | NONE      | NONE         |          |          |
| CONTAMINATION  There is no indication of any contamination in the oil.   | Silicon          | ppm    | ASTM D5185m | >75       | 14           |          |          |
|  | Potassium        | ppm    | ASTM D5185m | >20       | 0            |          |          |
|  | Water            |        | WC Method   | >0.075    | NEG          |          |          |
|  | Silt             | scalar | *Visual     | NONE      | NONE         |          |          |
|  | Debris           | scalar | *Visual     | NONE      | NONE         |          |          |
|  | Sand/Dirt        | scalar | *Visual     | NONE      | NONE         |          |          |
|  | Appearance       | scalar | *Visual     | NORML     | NORML        |          |          |
|  | Odor             | scalar | *Visual     | NORML     | NORML        |          |          |
|  | Emulsified Water | scalar | *Visual     | >0.075    | NEG          |          |          |
| FLUID CONDITION  The oil viscosity is higher than normal. This plus the additive levels indicates the addition of a different brand, or type of oil. Confirm oil type. | Sodium           | ppm    | ASTM D5185m | >51       | 6            |          |          |
|  | Boron            | ppm    | ASTM D5185m | 6         | <b>134</b>   |          |          |
|  | Barium           | ppm    | ASTM D5185m | 0         | 13           |          |          |
|  | Molybdenum       | ppm    | ASTM D5185m | 0         | 0            |          |          |
|  | Manganese        | ppm    | ASTM D5185m |           | <1           |          |          |
|  | Magnesium        | ppm    | ASTM D5185m | 145       | <b>2</b>     |          |          |
|  | Calcium          | ppm    | ASTM D5185m |           | <b>▲</b> 853 |          |          |
|  | Phosphorus       | ppm    | ASTM D5185m | 1290      | <b>▲</b> 694 |          |          |
|  | Zinc             | ppm    | ASTM D5185m | 1640      | 1616         |          |          |
|  | Sulfur           | ppm    | ASTM D5185m |           | 5551         |          |          |
|  | Visc @ 40°C      | cSt    | ASTM D445   | 57.0      | 83.7         |          |          |





Laboratory Sample No.

Lab Number : 06086267 Unique Number : 10873712

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : JR0195617

Received Tested Diagnosed Test Package : CONST ( Additional Tests: PQ )

: 12 Feb 2024 : 13 Feb 2024

: 13 Feb 2024 - Sean Felton

JRE - STEPHENSON 245 YARDMASTER COURT STEPHENSON, VA US 22656-1761

Contact: PHIL DAUGHERTY

To discuss this sample report, contact Customer Service at 1-800-237-1369. pdaugherty@jamesriverequipment.com \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: x:

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (540)693-2588