

WEAR CONTAMINATION **FLUID CONDITION**

NORMAL NORMAL NORMAL



BELL B45E B93A645EP03408183

Component Center Right Final Drive

GEAR OIL SAE 80W90 (GAL	_)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		BE0018057		
riesample at the next service interval to monitor.	Sample Date		Client Info		07 Feb 2024		
	Machine Age	hrs	Client Info		2016		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184	>3000	1028		
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>HR:1=	371		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>10	2		
	Nickel	ppm	ASTM D5185m	>10	3		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>25	4		
	Lead	ppm	ASTM D5185m	>25	<1		
	Copper	ppm	ASTM D5185m	>50	6		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	MODER		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>201	54		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	3		
	Water		WC Method	>1.01	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>1.01	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>170	<1		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	400	2		
The condition of the of is acceptable for the time in service.	Barium	ppm	ASTM D5185m	200	0		
	Molybdenum	ppm	ASTM D5185m	12	2		
	Manganese	ppm	ASTM D5185m		8		
	Magnesium	ppm	ASTM D5185m	12	19		
	Calcium	ppm	ASTM D5185m	150	95		
	Phosphorus	ppm	ASTM D5185m	1650	460		
	Zinc	ppm	ASTM D5185m	125	65		
	Sulfur	ppm	ASTM D5185m	22500	17485		
	Visc @ 40°C	cSt	ASTM D445	143	141		
Report Id: bened005 [WUSCAR] 06086279 (Generated: 02/13/2024 14:08:09) Rev: 1						Sub	mitted By: ?







Laboratory Sample No.

: BE0018057 Lab Number : 06086279 Unique Number : 10873724 Test Package : MOBCE

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 12 Feb 2024

: 13 Feb 2024 **Tested** Diagnosed

: 13 Feb 2024 - Sean Felton

National Equipment Dealers LLC NE 215 Woodside Drive Lexington, NC

US 27292 Contact: Steven Gawthrop

Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. sgawthrop@nedealers.com

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: F: