



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
KATHY AZLIN
Component
Starboard Main Engine
Fluid
CHEVRON DELO 400 SDE SAE 15W40 (165 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW0057951	MW0057965	MW0057963
Sample Date		Client Info		03 Feb 2024	01 Jan 2024	05 Dec 2023
Machine Age	hrs	Client Info		61438	60971	60482
Oil Age	hrs	Client Info		467	1436	985
Filter Age	hrs	Client Info		467	699	216
Oil Changed		Client Info		Changed	Changed	Not Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>75	4	5	4
Chromium	ppm	ASTM D5185m	>8	<1	0	0
Nickel	ppm	ASTM D5185m	>2	<1	0	0
Titanium	ppm	ASTM D5185m	>3	12	8	8
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>15	2	1	1
Lead	ppm	ASTM D5185m	>18	<1	0	0
Copper	ppm	ASTM D5185m	>80	5	7	5
Tin	ppm	ASTM D5185m	>14	<1	0	0
Vanadium	ppm	ASTM D5185m		<1	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>20	8	5	4
Potassium	ppm	ASTM D5185m	>20	3	2	2
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844		0.1	0.2	0.2
Nitration	Abs/cm	*ASTM D7624	>20	7.6	7.6	7.0
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.7	19.2	18.5
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>75	38	5	4
Boron	ppm	ASTM D5185m		214	224	240
Barium	ppm	ASTM D5185m		13	0	0
Molybdenum	ppm	ASTM D5185m		41	46	46
Manganese	ppm	ASTM D5185m		<1	<1	0
Magnesium	ppm	ASTM D5185m		511	437	413
Calcium	ppm	ASTM D5185m		2015	2275	2249
Phosphorus	ppm	ASTM D5185m	760	802	809	832
Zinc	ppm	ASTM D5185m	800	895	962	957
Sulfur	ppm	ASTM D5185m	3000	3639	3197	3283
Oxidation	Abs/.1mm	*ASTM D7414	>25	12.6	12.8	12.0
Base Number (BN)	mg KOH/g	ASTM D2896	10	8.4	8.3	8.2
Visc @ 100°C	cSt	ASTM D445	14.6	14.0	14.0	14.0



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : MW0057951
Lab Number : 06086609
Unique Number : 10874054
Test Package : MAR 2

Received : 12 Feb 2024
Tested : 13 Feb 2024
Diagnosed : 13 Feb 2024 - Don Baldrige

MAGNOLIA MARINE TRANSPORT
 697 HAINING ROAD
 VICKSBURG, MS
 US 39183
 Contact: MMT MAINTENANCE PLANNERS
 mmtmaintenanceplanners@ergon.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: x:
 F: (601)638-8028