
WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL

Area [LKQ LARGO] VOLVO L60H 622999

Component Diesel Engine

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		VCP440653	VCP420275	
	Sample Date		Client Info		12 Feb 2024	14 Apr 2023	
	Machine Age	hrs	Client Info		1230	472	
	Oil Age	hrs	Client Info		0	472	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Changed	Changed	
	Filter Changed		Client Info		Changed	Changed	
	Sample Status				NORMAL	NORMAL	
WEAR	Iron	ppm	ASTM D5185m	>100	16	14	
WLAN	Chromium		ASTM D5185m		2	2	
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		0	0	
	Titanium	ppm	ASTM D5185m	>10	0	0	
	Silver	ppm	ASTM D5185m	. 0		-	
		ppm			0	0	
	Aluminum	ppm	ASTM D5185m		7	5	
	Lead	ppm	ASTM D5185m		<1	0	
	Copper	ppm	ASTM D5185m		2	6	
	Tin	ppm	ASTM D5185m	>10	2	<1	
	Vanadium	ppm	ASTM D5185m	NONE	<1 NONE	0	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
<u></u>	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION	Silicon	ppm	ASTM D5185m	>20	10	14	
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	0	0	
	Fuel		WC Method	>6.0	<1.0	<1.0	
	Water		WC Method	>0.1	NEG	NEG	
	Glycol		WC Method		NEG	NEG	
	Soot %	%	*ASTM D7844	>3	0.4	0.2	
	Nitration	Abs/cm	*ASTM D7624	>20	7.1	6.0	
	Sulfation	Abs/.1mm	*ASTM D7415	>30	21.8	18.8	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	
LUID CONDITION	Sodium	ppm	ASTM D5185m		2	3	
ESIB SSRBITION	Boron	ppm	ASTM D5185m	2.5	38	51	
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		<1	0	
	Molybdenum	ppm	ASTM D5185m		44	41	
	Manganese	ppm	ASTM D5185m		<1	4	
	Magnesium	ppm	ASTM D5185m		535	657	
	Calcium	ppm	ASTM D5185m		1802	1494	
	Phosphorus	ppm	ASTM D5185m		993	976	
	Zinc	ppm	ASTM D5185m		1160	1167	
	Sulfur	ppm	ASTM D5185m		3146	4005	
	Oxidation	Abs/.1mm	*ASTM D7414		19.7	16.7	
	Base Number (BN)				9.9	9.2	
	Dado Hambor (DIV)	cSt	ASTM D445		12.8	12.9	





Laboratory Sample No.

Lab Number : 06086928

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : VCP440653

Unique Number : 10874373

Received : 13 Feb 2024 **Tested**

: 13 Feb 2024 : 13 Feb 2024 - Wes Davis Diagnosed Test Package : MOB 1 (Additional Tests: TBN)

1.0

ALTA EQUIPMENT/FLAGLER CONSTRUCTION EQUIPMENT LLC

8418 PALM RIVER ROAD TAMPA, FL US 33619

Contact: KENNY HANEY khaney@flaglerce.com T: (813)630-0077

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (813)630-2233