

WEAR NORMAL CONTAMINATION NORMAL FLUID CONDITION ATTENTION

JOHN DEERE 245P 1FF245PAANF000015

Component Rear Right Pump Drive

JÖHN DEERE GL-5 80W90 (2 QTS)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		JR0202214		
	Sample Date		Client Info		07 Feb 2024		
	Machine Age	hrs	Client Info		480		
	Oil Age	hrs	Client Info		480		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				ATTENTION		
WEAR	PQ		ASTM D8184		16		
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>500	<1		
	Chromium	ppm	ASTM D5185m	>15	<1		
	Nickel	ppm	ASTM D5185m	>10	<1		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>20	9		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m	>35	<1		
	Tin	ppm	ASTM D5185m	>4	<1		
	Vanadium	ppm	ASTM D5185m		1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>75	2		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	7		
	Water		WC Method	>0.2	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		26		
The oil viscosity is lower than normal. This plus the additive levels indicates the addition of a different brand, or type of oil. Confirm oil type.	Boron	ppm	ASTM D5185m		A 0		
	Barium	ppm	ASTM D5185m		2 7		
	Molybdenum	ppm	ASTM D5185m		<1		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		10		
	A				1 A A A A		

Calcium

Zinc

Sulfur

Phosphorus

Visc @ 40°C

ppm

ppm

ppm

ppm

cSt

ASTM D5185m

ASTM D5185m

ASTM D5185m

ASTM D5185m

ASTM D445


12


62

2

A 27

75.6





Submitted By: RALEIGH SHOP

Page 2 of 2