



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
JOHN DEERE 700L 1T0700LXPNF421273

Component
Right Final Drive
Fluid
NOT GIVEN (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0202793	JR0168004	JR0163558
Sample Date		Client Info		05 Feb 2024	04 May 2023	07 Mar 2023
Machine Age	hrs	Client Info		3429	2026	1702
Oil Age	hrs	Client Info		1403	1547	479
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	Changed	Not Changd
Filter Changed		Client Info		Not Changd	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184	>1250	38	40	49
Iron	ppm	ASTM D5185m	>750	38	76	54
Chromium	ppm	ASTM D5185m	>9	<1	2	1
Nickel	ppm	ASTM D5185m	>10	0	0	0
Titanium	ppm	ASTM D5185m		0	<1	<1
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>40	5	3	4
Lead	ppm	ASTM D5185m	>15	0	0	<1
Copper	ppm	ASTM D5185m	>40	0	0	<1
Tin	ppm	ASTM D5185m	>10	0	0	0
Vanadium	ppm	ASTM D5185m		<1	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	MODER
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>75	7	19	15
Potassium	ppm	ASTM D5185m	>20	4	1	3
Water		WC Method	>0.075	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m	>51	12	<1	0
Boron	ppm	ASTM D5185m		7	4	<1
Barium	ppm	ASTM D5185m		8	0	0
Molybdenum	ppm	ASTM D5185m		5	2	1
Manganese	ppm	ASTM D5185m		0	1	1
Magnesium	ppm	ASTM D5185m		62	98	92
Calcium	ppm	ASTM D5185m		852	3456	3480
Phosphorus	ppm	ASTM D5185m		477	1019	1020
Zinc	ppm	ASTM D5185m		529	1253	1201
Sulfur	ppm	ASTM D5185m		1939	4470	3435
Visc @ 40°C	cSt	ASTM D445		51.8	51.7	52.9



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0202793 **Received** : 13 Feb 2024
Lab Number : 06087675 **Tested** : 14 Feb 2024
Unique Number : 10875120 **Diagnosed** : 15 Feb 2024 - Angela Borella
Test Package : CONST (Additional Tests: PQ)

JRE - GARNER
 4161 AUBURN CHURCH RD
 GARNER, NC
 US 27529
 Contact: RALEIGH SHOP

To discuss this sample report, contact Customer Service at 1-800-237-1369.

sean.betts@jamesriverequipment.com; catherine.anastasio@wearcheck.com

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

T: (919)614-2260

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (919)779-5432