


NORMAL WEAR NORMAL CONTAMINATION FLUID CONDITION NORMAL

Machine Id

24B0703 ATF-025 Component New (Unused) Oil

NOT GIVEN (--- GAL)

	Teet		Mathad	Limit/Abn	Current	Llistond	Lliatory O
RECOMMENDATION	Test Sample Number	UOM	Method Client Info	Limit/Abn	Current HPL0000946	History1	History2
This is a baseline read-out on the submitted sample.	Sample Date		Client Info		08 Feb 2024		
'	Machine Age	hrs	Client Info		00 reb 2024		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m		0		
	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m		0		
	Titanium Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m ASTM D5185m		0		
	Lead	ppm	ASTM D5185m		1 0		
	Copper	ppm ppm	ASTM D5185m		0		
	Tin	ppm	ASTM D5185m		0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION							
	Silicon	ppm	ASTM D5185m		2		
	Potassium	ppm	ASTM D5185m	>20	<1		
	Water		WC Method	5000	NEG		
	Particles >4µm		ASTM D7647		2931		
	Particles >6µm		ASTM D7647		706		
	Particles >14µm Particles >21µm		ASTM D7647 ASTM D7647		21 2		
	Particles >38µm		ASTM D7647 ASTM D7647		0		
	Particles >71µm		ASTM D7647 ASTM D7647		0		
	Oil Cleanliness		ISO 4406 (c)		19/17/12		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual		NEG		
	0				•		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		0		
	Boron Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm ppm	ASTM D5185m ASTM D5185m		8 0		
	Manganese		ASTM D5185m		0		
	Magnesium	ppm ppm	ASTM D5185m		3		
	Calcium	ppm	ASTM D5185m		725		
	Phosphorus	ppm	ASTM D5185m		691		
	Zinc	ppm	ASTM D5185m		792		
	Sulfur	ppm	ASTM D5185m		5264		
	Acid Number (AN)	mg KOH/g	ASTM D8045		0.95		
	Visc @ 40°C	cSt	ASTM D445		46.05		
	Visc @ 100°C	cSt	ASTM D445		8.7		
	Viscosity Index (VI)				170		



HIGH PERFORMANCE LUBRICANTS LLC Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 500 S SPRUCE ST Sample No. : HPL0000946 Received : 13 Feb 2024 Ġ MANTENO, IL Lab Number : 06087854 Tested : 15 Feb 2024 : 15 Feb 2024 - Jonathan Hester Unique Number : 10875299 US 60950 Diagnosed Test Package : MOB 2 (Additional Tests: FT-IR, ICP-NewOil, KV100, PrtCount, VI) Contact: DAVID WARD Certificate L2367 sampledata@hplubricants.com To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (815)468-3535 F: x: Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Page 2 of 2