



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
JLG 1255 016-0118 (S/N 0160086959)

Component
Diesel Engine

Fluid
SCHAEFFER SUPREME 7000 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0868353	WC0868382	WC0868269
Sample Date		Client Info		25 Jan 2024	16 Nov 2023	27 Oct 2023
Machine Age	hrs	Client Info		12325	12098	11871
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>90	7	<1	2
Chromium	ppm	ASTM D5185m	>20	0	0	<1
Nickel	ppm	ASTM D5185m	>2	<1	0	0
Titanium	ppm	ASTM D5185m	>2	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>20	4	2	4
Lead	ppm	ASTM D5185m	>40	0	0	<1
Copper	ppm	ASTM D5185m	>330	0	0	0
Tin	ppm	ASTM D5185m	>15	<1	0	<1
Vanadium	ppm	ASTM D5185m		<1	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	6	4	4
Potassium	ppm	ASTM D5185m	>20	<1	0	<1
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>6	0.1	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>20	8.2	8.0	8.3
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.0	17.9	18.1
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	3	2
Boron	ppm	ASTM D5185m		84	81	74
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m	50	73	72	72
Manganese	ppm	ASTM D5185m		0	0	0
Magnesium	ppm	ASTM D5185m	1000	17	14	17
Calcium	ppm	ASTM D5185m	1400	2123	2116	2245
Phosphorus	ppm	ASTM D5185m	985	1064	1036	1103
Zinc	ppm	ASTM D5185m	1060	1261	1260	1366
Sulfur	ppm	ASTM D5185m	4000	5233	4904	5492
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.4	14.1	14.3
Base Number (BN)	mg KOH/g	ASTM D2896	10	6.4	6.3	6.5
Visc @ 100°C	cSt	ASTM D445	15	14.3	14.3	14.2



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0868353 **Received** : 13 Feb 2024
Lab Number : 06088056 **Tested** : 14 Feb 2024
Unique Number : 10875501 **Diagnosed** : 14 Feb 2024 - Wes Davis
Test Package : CONST (Additional Tests: TBN)

SHIMMICK CONSTRUCTION
 5535 TRAILHEAD DRIVE
 CHATTANOOGA, TN
 US 37415
 Contact: DANIEL LISELLA
 daniel.lisella@shimmick.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: