



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area  
**[W05004053]**  
Machine Id  
**VOLVO EC750 314245**  
Component  
**Rear Right Final Drive**  
Fluid  
**VOLVO PREMIUM GEAR OIL 85W-140 GL-5 (2 GAL)**

**RECOMMENDATION**

Resample at the next service interval to monitor. ( Customer Sample Comment: W05004053 1000 hour service )

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>ML0000425</b>	---	---
Sample Date		Client Info		<b>09 Feb 2024</b>	---	---
Machine Age	hrs	Client Info		<b>1022</b>	---	---
Oil Age	hrs	Client Info		<b>500</b>	---	---
Filter Age	hrs	Client Info		<b>0</b>	---	---
Oil Changed		Client Info		<b>Changed</b>	---	---
Filter Changed		Client Info		<b>N/A</b>	---	---
Sample Status				<b>NORMAL</b>	---	---

**WEAR**

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>500	<b>348</b>	---	---
Chromium	ppm	ASTM D5185m	>10	<b>5</b>	---	---
Nickel	ppm	ASTM D5185m	>10	<b>&lt;1</b>	---	---
Titanium	ppm	ASTM D5185m		<b>&lt;1</b>	---	---
Silver	ppm	ASTM D5185m		<b>0</b>	---	---
Aluminum	ppm	ASTM D5185m	>25	<b>4</b>	---	---
Lead	ppm	ASTM D5185m	>25	<b>0</b>	---	---
Copper	ppm	ASTM D5185m	>50	<b>0</b>	---	---
Tin	ppm	ASTM D5185m	>10	<b>0</b>	---	---
Vanadium	ppm	ASTM D5185m		<b>0</b>	---	---
White Metal	scalar	*Visual	NONE	<b>NONE</b>	---	---
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	---	---

**CONTAMINATION**





There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>75	<b>35</b>	---	---
Potassium	ppm	ASTM D5185m	>20	<b>3</b>	---	---
Water		WC Method	>0.2	<b>NEG</b>	---	---
Silt	scalar	*Visual	NONE	<b>NONE</b>	---	---
Debris	scalar	*Visual	NONE	<b>NONE</b>	---	---
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	---	---
Appearance	scalar	*Visual	NORML	<b>NORML</b>	---	---
Odor	scalar	*Visual	NORML	<b>NORML</b>	---	---
Emulsified Water	scalar	*Visual	>0.2	<b>NEG</b>	---	---

**FLUID CONDITION**

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		<b>2</b>	---	---
Boron	ppm	ASTM D5185m	111	<b>0</b>	---	---
Barium	ppm	ASTM D5185m	0.0	<b>13</b>	---	---
Molybdenum	ppm	ASTM D5185m	0.9	<b>0</b>	---	---
Manganese	ppm	ASTM D5185m	0.0	<b>6</b>	---	---
Magnesium	ppm	ASTM D5185m	39	<b>&lt;1</b>	---	---
Calcium	ppm	ASTM D5185m	93	<b>17</b>	---	---
Phosphorus	ppm	ASTM D5185m	920	<b>343</b>	---	---
Zinc	ppm	ASTM D5185m	104	<b>4</b>	---	---
Sulfur	ppm	ASTM D5185m	20179	<b>16308</b>	---	---
Visc @ 40°C	cSt	ASTM D445	333	<b>177</b>	---	---



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : ML0000425  
**Lab Number** : 06088400  
**Unique Number** : 10875845  
**Test Package** : CONST

**Received** : 13 Feb 2024  
**Tested** : 14 Feb 2024  
**Diagnosed** : 15 Feb 2024 - Sean Felton

**MCCLUNG-LOGAN EQUIPMENT CO - MANASSAS**  
 8450 QUARRY ROAD  
 MANASSAS, VA  
 US 20110  
 Contact: DARRELL ANDES  
 dandes@mcclung-logan.com  
 T:  
 F: (703)393-7844

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)