



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
ST JOHNS GEN 1
 Component
Diesel Engine
 Fluid
SHELL ROTELLA T 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0872213	LF0001298	LF0000296
Sample Date		Client Info		05 Jan 2024	28 Jan 2023	07 Jan 2021
Machine Age	hrs	Client Info		7	12	17
Oil Age	hrs	Client Info		7	12	0
Filter Age	hrs	Client Info		7	12	0
Oil Changed		Client Info		N/A	Changed	Changed
Filter Changed		Client Info		N/A	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

Metal levels are typical for a new component breaking in.

Iron	ppm	ASTM D5185m	>90	2	3	3
Chromium	ppm	ASTM D5185m	>20	<1	<1	<1
Nickel	ppm	ASTM D5185m	>2	0	0	<1
Titanium	ppm	ASTM D5185m	>2	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	<1
Aluminum	ppm	ASTM D5185m	>20	1	0	<1
Lead	ppm	ASTM D5185m	>40	0	1	2
Copper	ppm	ASTM D5185m	>330	<1	<1	1
Tin	ppm	ASTM D5185m	>15	0	0	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	2	2	1
Potassium	ppm	ASTM D5185m	>20	9	8	7
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>6	0.1	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>20	5.4	6.2	6.5
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.3	21.0	21
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		0	2	1
Boron	ppm	ASTM D5185m	316	203	214	186
Barium	ppm	ASTM D5185m	0.0	8	0	0
Molybdenum	ppm	ASTM D5185m	1.2	0	<1	<1
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m	24	11	10	12
Calcium	ppm	ASTM D5185m	2292	1928	2085	2076
Phosphorus	ppm	ASTM D5185m	1064	849	961	971
Zinc	ppm	ASTM D5185m	1160	1062	1110	1136
Sulfur	ppm	ASTM D5185m	4996	3370	3414	3057
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.6	16.9	16.7
Base Number (BN)	mg KOH/g	ASTM D2896	10.1	8.8	8.9	---
Visc @ 100°C	cSt	ASTM D445	15.7	14.3	14.7	14.8



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0872213
Lab Number : 06088499
Unique Number : 10875944
Test Package : FLEET

Received : 14 Feb 2024
Tested : 15 Feb 2024
Diagnosed : 15 Feb 2024 - Wes Davis

STANDBY POWER SUPPORT SYSTEMS
 6100 COLORADO AVE
 ODESSA, TX
 US 79760

Contact: SANTANA SARABIA
 standbypower7114@yahoo.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (432)362-1051
 F: (432)362-1052