WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL





JOHN DEERE 724K 1DW724KZLGF674537


Component Diesel Engine


JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (7 GAL)


JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (7 GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
HEGOMMENDATION	Sample Number		Client Info		JR0203496		JR0143713
Resample at the next service interval to monitor.	Sample Date		Client Info		08 Feb 2024	08 Feb 2024	15 Sep 2022
	Machine Age	hrs	Client Info		6898	6898	6603
	Oil Age	hrs	Client Info		5904	0	0
	Filter Age	hrs	Client Info		0	0	0
	Oil Changed		Client Info		Changed	Not Changd	N/A
	Filter Changed		Client Info		Changed	Not Changd	N/A
	Sample Status				NORMAL	NORMAL	NORMAL
WEAR	Iron	ppm	ASTM D5185m	<u></u>	41	7	60
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1	<1	2
	Nickel	ppm	ASTM D5185m		5	0	3
	Titanium	ppm	ASTM D5185m	75	<1	<1	<1
	Silver	ppm	ASTM D5185m	~3	0	0	0
	Aluminum	ppm	ASTM D5185m		3	3	7
	Lead	ppm	ASTM D5185m		0	0	3
	Copper	ppm	ASTM D5185m		1	<1	4
	Tin	ppm		>4	0	0	<1
	Vanadium	ppm	ASTM D5185m		0	<1	<1
	White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185m	>22	6	7	11
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	7	3	6
	Fuel		WC Method	>2.1	<1.0	<1.0	<1.0
	Water		WC Method	>0.21	NEG	NEG	NEG
	Glycol		WC Method		NEG	NEG	NEG
	Soot %	%	*ASTM D7844	>3	0.2	0.1	0.8
	Nitration	Abs/cm	*ASTM D7624	>20	6.7	5.5	11.0
	Sulfation	Abs/.1mm	*ASTM D7415	>30	20.0	19.6	27.8
	Silt	scalar	*Visual	NONE	NONE	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
	Odor	scalar	*Visual	NORML	NORML	NORML	NORML
	Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>31	0	0	2
	Boron	ppm	ASTM D5185m		211	308	43
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		12	0	0
	Molybdenum	ppm	ASTM D5185m		94	242	236
	Manganese	ppm	ASTM D5185m		<1	0	<1
	Magnesium	ppm	ASTM D5185m		300	708	746
	Calcium	ppm	ASTM D5185m		1803	1280	1530
	Phosphorus	ppm	ASTM D5185m		966	813	783
	Zinc	ppm	ASTM D5185m		1103	1021	1015
	Sulfur	ppm	ASTM D5185m		3812	2726	3408
	Oxidation	Abs/.1mm	*ASTM D7414		15.6	14.1	20.9
	Base Number (BN)	mg KOH/g			8.6	9.7	8.7
	Visc @ 100°C	cSt	ASTM D445	15.4	13.6	14.2	13.3
















Report Id: JAMCHA [WUSCAR] 06088633 (Generated: 02/22/2024 18:13:34) Rev: 1

Laboratory Sample No. Lab Number : 06088633 Unique Number : 10876078

: JR0203496

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Received **Tested** Diagnosed

: 14 Feb 2024 : 15 Feb 2024

: 15 Feb 2024 - Sean Felton

JRE - CHARLOTTE 9550 STATESVILLE ROAD

CHARLOTTE, NC US 28269

Contact: CHARLOTTE SHOP myoung@jamesriverequipment.com

T: (704)597-0211 F: (704)596-6198

Test Package : CONST (Additional Tests: TBN) To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)