



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>



Area  
**MONTGOMERY**  
Machine Id  
**MACK 920016-192537**  
Component  
**Diesel Engine**  
Fluid  
**PETRO CANADA DURON SHP 15W40 (--- LTR)**

**RECOMMENDATION**

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>GFL0088637</b>	GFL0088640	GFL0088667
Sample Date		Client Info		<b>09 Feb 2024</b>	06 Feb 2024	02 Feb 2024
Machine Age	hrs	Client Info		<b>11402</b>	11370	11322
Oil Age	hrs	Client Info		<b>32</b>	273	225
Filter Age	hrs	Client Info		<b>0</b>	0	0
Oil Changed		Client Info		<b>Not Chngd</b>	Changed	N/A
Filter Changed		Client Info		<b>N/A</b>	Changed	N/A
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

**WEAR**

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>120	<b>4</b>	17	11
Chromium	ppm	ASTM D5185m	>20	<b>&lt;1</b>	1	<1
Nickel	ppm	ASTM D5185m	>5	<b>0</b>	1	1
Titanium	ppm	ASTM D5185m	>2	<b>&lt;1</b>	<1	0
Silver	ppm	ASTM D5185m	>2	<b>0</b>	0	0
Aluminum	ppm	ASTM D5185m	>20	<b>2</b>	1	2
Lead	ppm	ASTM D5185m	>40	<b>0</b>	<1	<1
Copper	ppm	ASTM D5185m	>330	<b>&lt;1</b>	3	2
Tin	ppm	ASTM D5185m	>15	<b>0</b>	<1	<1
Vanadium	ppm	ASTM D5185m		<b>0</b>	0	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

**CONTAMINATION**







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	<b>4</b>	6	4
Potassium	ppm	ASTM D5185m	>20	<b>2</b>	2	4
Fuel		WC Method	>3.0	<b>&lt;1.0</b>	<1.0	<1.0
Water		WC Method	>0.2	<b>NEG</b>	NEG	NEG
Glycol		WC Method		<b>NEG</b>	NEG	NEG
Soot %	%	*ASTM D7844	>4	<b>0.2</b>	0.9	0.9
Nitration	Abs/cm	*ASTM D7624	>20	<b>4.9</b>	8.9	8.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>17.5</b>	19.0	18.9
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	<b>NEG</b>	NEG	NEG

**FLUID CONDITION**

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>0</b>	0	4
Boron	ppm	ASTM D5185m	0	<b>0</b>	4	3
Barium	ppm	ASTM D5185m	0	<b>12</b>	0	0
Molybdenum	ppm	ASTM D5185m	60	<b>58</b>	66	60
Manganese	ppm	ASTM D5185m	0	<b>0</b>	<1	1
Magnesium	ppm	ASTM D5185m	1010	<b>914</b>	1016	909
Calcium	ppm	ASTM D5185m	1070	<b>1065</b>	1129	993
Phosphorus	ppm	ASTM D5185m	1150	<b>1121</b>	1077	1029
Zinc	ppm	ASTM D5185m	1270	<b>1175</b>	1317	1233
Sulfur	ppm	ASTM D5185m	2060	<b>3864</b>	3245	2985
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>13.2</b>	14.1	14.0
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	<b>8.9</b>	7.3	7.6
Visc @ 100°C	cSt	ASTM D445	15.4	<b>14.2</b>	13.6	13.6



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : GFL0088637  
**Lab Number** : 06088649  
**Unique Number** : 10876094  
**Test Package** : FLEET

**Received** : 14 Feb 2024  
**Tested** : 15 Feb 2024  
**Diagnosed** : 15 Feb 2024 - Wes Davis

**GFL Environmental - 955 - Montgomery**  
 1121 Wilbanks St  
 Montgomery, AL  
 US 36108  
 Contact: LISA REEVES

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:  
F: