**WEAR CONTAMINATION FLUID CONDITION** 

**NORMAL NORMAL** NORMAL

## JOHN DEERE 544 P 1DW544PAJPLX20402

Component Front Axle

Front Axle TDH FLUID SAE 75W80 ( GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) TDH FLUID SAE 75W80. Please confirm.	Sample Number		Client Info		JR0203440		
	Sample Date		Client Info		13 Feb 2024		
	Machine Age	hrs	Client Info		523		
	Oil Age	hrs	Client Info		523		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184		16		
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>750	39		
	Chromium	ppm	ASTM D5185m	>11	<1		
	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>21	2		
	Lead	ppm	ASTM D5185m	>49	23		
	Copper	ppm	ASTM D5185m	>101	62		
	Tin	ppm	ASTM D5185m	>10	<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>31	6		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	2		
	Water		WC Method	>0.1	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	0		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	10	<1		
	Barium	ppm	ASTM D5185m	10	16		
	Molybdenum	ppm	ASTM D5185m	10	<1		
	Manganese	ppm	ASTM D5185m		4		
	Magnesium	ppm	ASTM D5185m	100	99		
	Calcium	ppm	ASTM D5185m	3500	3526		
	Phosphorus	ppm	ASTM D5185m	1150	1186		
	Zinc	ppm	ASTM D5185m		1226		
	Sulfur	ppm	ASTM D5185m		5402		
	Visc @ 40°C	cSt	ASTM D445	48	54.0		
Report Id: CARCHAJR [WUSCAR] 06089099 (Generated: 02/15/2024 05:02:11) Rev: 1					Sul	omitted By:	Ray Benson





Laboratory Sample No.

Lab Number : 06089099 Unique Number : 10876544

: JR0203440

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Received **Tested** Diagnosed

: 14 Feb 2024 : 15 Feb 2024

: 15 Feb 2024 - Wes Davis

9550 STATESVILLE ROAD CHARLOTTE, NC US 28269

Contact: LEO

F:

T: (704)547-0211

Test Package : CONST ( Additional Tests: PQ ) To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)