WEAR CONTAMINATION **FLUID CONDITION**

NORMAL NORMAL NORMAL




144689-1528 LIEBHERR LI	H60C 1446	89-1	528				
Front Left Final Drive	,						
GEAR OIL SAE 80W90 (GAL	.)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		LH0267325		
	Sample Date		Client Info		09 Feb 2024		
	Machine Age	hrs	Client Info		2403		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR All component wear rates are normal.	Iron	ppm	ASTM D5185m	>500	44		
	Chromium	ppm	ASTM D5185m	>10	<1		
	Nickel	ppm	ASTM D5185m	>10	<1		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>25	2		
	Lead	ppm	ASTM D5185m	>25	<1		
	Copper	ppm	ASTM D5185m	>50	9		
	Tin	ppm	ASTM D5185m	>10	<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	MODER		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	nnm	ASTM D5185m	· 75	2		
	Potassium	ppm	ASTM D5185m		2		
There is no indication of any contamination in the oil.	Water	ppiii	WC Method		NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar		NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water		*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		<1		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		0		
	Barium	ppm	ASTM D5185m		16		
	Molybdenum	ppm	ASTM D5185m	12	<1		
	Manganese	ppm	ASTM D5185m	10	<1		
	Magnesium	ppm	ASTM D5185m		2		
	Calcium	ppm	ASTM D5185m		39		
	Phosphorus	ppm	ASTM D5185m		1165		
	Zinc	ppm	ASTM D5185m		5		
	Sulfur	ppm	ASTM D5185m	22500	29200		


Visc @ 40°C


131

ASTM D445 143











Certificate L2367

Laboratory Sample No.

Lab Number : 06089170

: LH0267325 Unique Number : 10876615 Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 14 Feb 2024 **Tested**

: 15 Feb 2024 : 15 Feb 2024 - Wes Davis Diagnosed

RIVER METALS RECYCLING - LOUISVILLE PO BOX 6521 LOUISVILLE, KY

US 40206 Contact: RYAN BOWDEN

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: RIVLOU [WUSCAR] 06089170 (Generated: 02/22/2024 13:28:47) Rev: 1

Contact/Location: RYAN BOWDEN - RIVLOU

F: (502)587-8699