WEAR CONTAMINATION **FLUID CONDITION**


NORMAL NORMAL ATTENTION

Machine Id

21

Component Diesel Engine

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
RECOMMENDATION	Sample Number	OOW	Client Info	LIIIIII/ADII	WC0632531		
Resample at the next service interval to monitor.	Sample Date		Client Info		23 Sep 2023		
	Machine Age	mls	Client Info		56669		
	Oil Age	mls	Client Info		5100		
	Filter Age	mls	Client Info		5100		
	Oil Changed	11110	Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status		One it into		ATTENTION		
VEAR	Iron	ppm	ASTM D5185m	>100	4		
	Chromium	ppm	ASTM D5185m	>20	<1		
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m	>3	0		
	Aluminum	ppm	ASTM D5185m		2		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		1		
	Tin	ppm	ASTM D5185m		1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>25	9		
	Potassium	ppm	ASTM D5185m	>20	3		
There is no indication of any contamination in the oil.	Fuel		WC Method		<1.0		
	Water		WC Method	>0.2	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	*ASTM D7844	>3	0		
	Nitration	Abs/cm	*ASTM D7624	>20	11.5		
	Sulfation	Abs/.1mm	*ASTM D7415	>30	23.0		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
LUID CONDITION	Sodium	ppm	ASTM D5185m		2		
	Boron	ppm	ASTM D5185m		4 0		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		A 72		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		952		
	Calcium	ppm	ASTM D5185m		1106		
	Phosphorus	ppm	ASTM D5185m		670		
	Zinc	ppm	ASTM D5185m		A 811		
	Sulfur	ppm	ASTM D5185m		2844		
	Oxidation	Abs/.1mm	*ASTM D7414	>25	16.1		
	Base Number (BN)		ASTM D2896	12.2	6.0		
	Visc @ 100°C	- 0	ASTM D445		10.4		





Laboratory Sample No.

: WC0632531 Lab Number : 06089285

Unique Number: 10876730

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 14 Feb 2024 : 15 Feb 2024 **Tested**

: 16 Feb 2024 - Jonathan Hester

Diagnosed Test Package : MOB 1 (Additional Tests: TBN)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

PRO-CARE IRRIGATION & TURF

5746 OLD LIBERTY RD FRANKLINVILLE, NC

US 27248 Contact: DEREK ROUTH

derekrouth72@gmail.com T: (336)736-6652