



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area

[44841]

Machine Id

JOHN DEERE 245G 1FF245GXVJF801010

Component

Diesel Engine

Fluid

JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (--- QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0195892	JR0176076	JR0154631
Sample Date		Client Info		13 Feb 2024	13 Jul 2023	05 Dec 2022
Machine Age	hrs	Client Info		5915	5404	4936
Oil Age	hrs	Client Info		511	500	478
Filter Age	hrs	Client Info		0	500	0
Oil Changed		Client Info		Changed	Changed	N/A
Filter Changed		Client Info		Changed	Changed	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>51	6	13	4
Chromium	ppm	ASTM D5185m	>11	0	<1	0
Nickel	ppm	ASTM D5185m	>5	0	0	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>31	7	10	4
Lead	ppm	ASTM D5185m	>26	<1	<1	<1
Copper	ppm	ASTM D5185m	>26	<1	2	1
Tin	ppm	ASTM D5185m	>4	<1	<1	<1
Vanadium	ppm	ASTM D5185m		<1	<1	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>22	6	11	7
Potassium	ppm	ASTM D5185m	>20	1	1	0
Fuel		WC Method	>2.1	<1.0	<1.0	<1.0
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.3	0.3	0.2
Nitration	Abs/cm	*ASTM D7624	>20	8.0	8.1	8.4
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.1	21.2	21.9
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>31	<1	1	1
Boron	ppm	ASTM D5185m		201	233	266
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		224	249	246
Manganese	ppm	ASTM D5185m		<1	1	<1
Magnesium	ppm	ASTM D5185m		719	917	823
Calcium	ppm	ASTM D5185m		1229	1529	1465
Phosphorus	ppm	ASTM D5185m		822	978	882
Zinc	ppm	ASTM D5185m		964	1208	1033
Sulfur	ppm	ASTM D5185m		2713	3985	3560
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.6	15.8	16.0
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	9.3	9.3	10.5
Visc @ 100°C	cSt	ASTM D445	15.4	13.8	14.0	13.9



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0195892 **Received** : 14 Feb 2024
Lab Number : 06089433 **Tested** : 15 Feb 2024
Unique Number : 10876878 **Diagnosed** : 16 Feb 2024 - Don Baldrige
Test Package : CONST (Additional Tests: TBN)

CWS-STRITTMATTER
 9102 OWENS DR
 MANASSAS PARK, VA
 US 20111

Contact: EDDIE GARRETSON
 egarretson@strittmattercompanies.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (703)335-2255
 F: (703)335-8095