



WEAR CHECK

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	SEVERE
FLUID CONDITION	NORMAL

Area

[62005694948]

Machine Id

14

Component

Diesel Engine

Fluid

DIESEL ENGINE OIL SAE 15W40 (--- QTS)

RECOMMENDATION

We advise that you check the fuel injection system. The oil change at the time of sampling has been noted. We recommend an early resample to monitor this condition. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0828093	WC0799983	WC0723340
Sample Date		Client Info		20 Nov 2023	24 Apr 2023	21 Sep 2022
Machine Age	mls	Client Info		134660	124303	114422
Oil Age	mls	Client Info		0	0	0
Filter Age	mls	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	N/A
Filter Changed		Client Info		Changed	Changed	N/A
Sample Status				SEVERE	SEVERE	SEVERE

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	24	64	77
Chromium	ppm	ASTM D5185m	>20	<1	2	3
Nickel	ppm	ASTM D5185m	>4	<1	<1	2
Titanium	ppm	ASTM D5185m		66	<1	<1
Silver	ppm	ASTM D5185m	>3	0	0	<1
Aluminum	ppm	ASTM D5185m	>20	8	16	15
Lead	ppm	ASTM D5185m	>40	2	2	6
Copper	ppm	ASTM D5185m	>330	0	<1	1
Tin	ppm	ASTM D5185m	>15	<1	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is a high amount of fuel present in the oil. Tests confirm the presence of fuel in the oil.

Silicon	ppm	ASTM D5185m	>25	6	6	6
Potassium	ppm	ASTM D5185m	>20	3	2	4
Fuel	%	ASTM D3524	>5	9.1	15.2	13.9
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	1.5	3.3	4.4
Nitration	Abs/cm	*ASTM D7624	>20	9.4	14.2	17.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.9	29.6	33.8
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The oil is no longer serviceable due to the presence of contaminants.

Sodium	ppm	ASTM D5185m	>158	2	5	5
Boron	ppm	ASTM D5185m	250	105	38	29
Barium	ppm	ASTM D5185m	10	0	0	0
Molybdenum	ppm	ASTM D5185m	100	6	8	9
Manganese	ppm	ASTM D5185m		<1	<1	1
Magnesium	ppm	ASTM D5185m	450	383	582	541
Calcium	ppm	ASTM D5185m	3000	1412	1121	1040
Phosphorus	ppm	ASTM D5185m	1150	889	885	831
Zinc	ppm	ASTM D5185m	1350	1038	1040	989
Sulfur	ppm	ASTM D5185m	4250	3334	3722	3275
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.1	23.4	25.7
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	9.7	8.7	10.0
Visc @ 100°C	cSt	ASTM D445	14.4	12.6	11.4	11.5



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0828093 **Received** : 14 Feb 2024
Lab Number : 06089470 **Tested** : 19 Feb 2024
Unique Number : 10876915 **Diagnosed** : 19 Feb 2024 - Wes Davis
Test Package : FLEET (Additional Tests: PercentFuel)

CASWELL COUNTY SCHOOL BUS
 353 COUNTY HOME ROAD
 YANCEYVILLE, NC
 US 27379
 Contact: DEBRA MOORE
 debra.moore@caswell.k12.nc.us
 T: (336)694-4116
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)